



Technical and Test Institute  
for Construction Prague  
Prosecká 811/76a  
190 00 Prague  
Czech Republic  
eota@tzus.cz



www.eota.eu

## European Technical Assessment

**ETA 21/0303  
of 12/04/2021**

(English language translation, the original version in Czech language)

**Technical Assessment Body issuing the ETA:** Technical and Test Institute for Construction Prague

**Trade name of the construction product**

RESINA POLIESTER SIN ESTIRENO LUSAN

**Product family to which the construction product belongs**

Product area code: 33  
Bonded injection type anchor for use in uncracked concrete

**Manufacturer**

LUSAN fijaciones y anclajes  
Molinos 20  
29491 Algarocín Málaga  
Spain

**Manufacturing plant(s)**

Plant 1

**This European Technical Assessment contains**

15 pages including 12 Annexes which form an integral part of this assessment.

**This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of**

EAD 330499-01-0601 Bonded fasteners for use in concrete

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such.

## **1. Technical description of the product**

The RESINA POLIESTER SIN ESTIRENO LUSAN POLIS, POLISB, POLIST and POLISE for uncracked concrete is a bonded anchor consisting of a cartridge with injection mortar and a steel element. The steel elements consists of a commercial threaded rods, a hexagon nut and a washer. The steel elements are made of galvanized steel or stainless steel.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The illustration and the description of the product are given in Annex A.

## **2. Specification of the intended use in accordance with the applicable EAD**

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The provisions made in this European Technical Assessment are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the products in relation to the expected economically reasonable working life of the works.

## **3. Performance of the product and references to the methods used for its assessment**

### **3.1 Mechanical resistance and stability (BWR 1)**

<b>Essential characteristic</b>	<b>Performance</b>
Characteristic resistance to tension load (static and quasi-static loading)	Annex C1, C2
Characteristic resistance to shear load (static and quasi-static loading)	Annex C1, C3
Displacements under short term and long term loading	Annex C4
Durability	Annex B1
Characteristic resistance and displacements for seismic performance categories C1 and C2	NPA

### **3.2 Hygiene, health and environment (BWR 3)**

No performance determined.

### **3.3 General aspects relating to fitness for use**

Durability and serviceability are only ensured if the specifications of intended use according to Annex B1 are kept.

## **4. Assessment and verification of constancy of performance (AVCP) system applied with reference to its legal base**

According to the Decision 96/582/EC of the European Commission<sup>1</sup> the system of assessment verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table applies.

<b>Product</b>	<b>Intended use</b>	<b>Level or class</b>	<b>System</b>
Metal anchors for use in concrete	For fixing and/or supporting to concrete, structural elements (which contributes to the stability of the construction works) or heavy units	-	1

<sup>1</sup> Official Journal of the European Communities L 254 of 08.10.1996

**5. Technical details necessary for the implementation of the AVCP system, as provided in the applicable EAD**

**5.1 Tasks of the manufacturer**

The manufacturer may only use raw materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the control plan which is a part of the technical documentation of this European Technical Assessment. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Technický a zkušební ústav stavební Praha, s.p.<sup>2</sup> The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

**5.2 Tasks of the notified bodies**

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The notified certification body involved by the manufacturer shall issue a certificate of constancy of performance of the product stating the conformity with the provisions of this European Technical assessment.

In cases where the provisions of the European Technical Assessment and its control plan are no longer fulfilled the notified body shall withdraw the certificate of constancy of performance and inform Technický a zkušební ústav stavební Praha, s.p without delay.

Issued in Prague on 12.04.2021

By


**Ing. Mária Schaan**

Head of the Technical Assessment Body

---

<sup>2</sup> The control plan is a confidential part of the documentation of the European Technical Assessment, but not published together with the ETA and only handed over to the approved body involved in the procedure of AVCP.

### Installation threaded rod



- $d_f$  = diameter of clearance hole in the fixture  
 $t_{fix}$  = thickness of fixture  
 $h_{ef}$  = effective embedment depth  
 $h_0$  = depth of drill hole  
 $h_{min}$  = minimum thickness of member


**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Installed conditions


**Annex A 1**

## **Cartridge: POLIS, POLISB, POLIST, POLISE**


**150 ml, 280 ml, 300 ml up to 330 ml and 380 ml up to 420 ml cartridge (Type: coaxial)**



**235 ml, 345 ml up to 360 ml and 825 ml cartridge (Type: "side-by-side")**



**165 ml and 300 ml cartridge (Type: "foil tube")**



## **Static mixer**

**SM 14W**




**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Injection system

**Annex A 2**

## Threaded rod M8, M10, M12, M16, M20, M24 with washer and hexagon nut



Commercial standard threaded rod with:

- Materials, dimensions and mechanical properties acc. Table A1
- Inspection certificate 3.1 acc. to EN 10204:2004
- Marking of embedment depth

**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Threaded rod

**Annex A 3**

**Table A1: Materials**

Part	Designation	Material
<b>Steel, zinc plated ( Steel acc. to EN 10087:1998 or EN 10263:2001)</b>		
zinc plated $\geq 5 \mu\text{m}$ acc. to EN ISO 4042:1999 or hot-dip galvanised $\geq 40 \mu\text{m}$ acc. to EN ISO 1461:2009 and EN ISO 10684:2004+AC:2009 or sherardized $\geq 40 \mu\text{m}$ acc. to EN ISO 17668:2016		
1	Anchor rod	4.6 $f_{uk}=400 \text{ N/mm}^2; f_{yk}=240 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		4.8 $f_{uk}=400 \text{ N/mm}^2; f_{yk}=320 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		5.6 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=300 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		5.8 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=400 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		8.8 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=640 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
2	Hexagon nut	Property class 4 for anchor rod class 4.6 or 4.8
		acc. to EN ISO 898-2:2012 5 for anchor rod class 5.6 or 5.8
		8 for anchor rod class 8.8
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	Steel, zinc plated, hot-dip galvanised or sherardized
<b>Stainless steel A2 (Material 1.4301 / 1.4311 / 1.4307 / 1.4567 or 1.4541, acc. to EN 10088-1:2014)</b>		
<b>and</b>		
<b>Stainless steel A4 (Material 1.4401 / 1.4404 / 1.4571 / 1.4362 or 1.4578, acc. to EN 10088-1:2014)</b>		
1	Anchor rod <sup>1)</sup>	Property class 50 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=210 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		acc. to EN ISO 3506-1:2009 70 $f_{uk}=700 \text{ N/mm}^2; f_{yk}=450 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		80 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=600 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
2	Hexagon nut <sup>1)</sup>	Property class 50 for anchor rod class 50
		acc. to EN ISO 3506-1:2009 70 for anchor rod class 70
		80 for anchor rod class 80
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	A2: Material 1.4301, 1.4311 / 1.4307 / 1.4567 or 1.4541, EN 10088-1:2014 A4: Material 1.4401, 1.4404 / 1.4571 / 1.4362 or 1.4578, EN 10088-1:2014
<b>High corrosion resistance steel (Material 1.4529 or 1.4565, acc. to EN 10088-1: 2014)</b>		
1	Anchor rod	Property class 50 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=210 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		acc. to EN ISO 3506-1:2009 70 $f_{uk}=700 \text{ N/mm}^2; f_{yk}=450 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
		80 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=600 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
2	Hexagon nut	Property class 50 for anchor rod class 50
		acc. to EN ISO 3506-1:2009 70 for anchor rod class 70
		80 for anchor rod class 80
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	Material 1.4529 or 1.4565, acc. to EN 10088-1: 2014

<sup>1)</sup> Strength class 80 only for stainless steel A4 + high corrosion resistance steel HCR

**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Materials

**Annex A 4**

## Specifications of intended use

### Anchorage subject to:

- Static and quasi-static loads

### Base materials:

- Reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013+A1:2016.
- Strength classes C20/25 to C50/60 according to EN 206:2013+A1:2016.
- Uncracked concrete

### Temperature range:

- T1: - 40 °C to +40 °C (max long term temperature +24 °C and max short term temperature +40 °C)
- T2: - 40 °C to +80 °C (max long term temperature +50 °C and max short term temperature +80 °C)

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (all materials)
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance class:
  - Stainless steel class A2 according to Annex A 4, Table A1: CRC II
  - Stainless steel class A4 according to Annex A 4, Table A1: CRC III
  - High corrosion resistance steel HCR according to Annex A 4, Table A1: CRC V

### Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Anchorages under static or quasi-static actions are designed in accordance with EN 1992-4

### Concrete condition:

- I1 – installation in dry or wet (water saturated) concrete and use in service in dry or wet concrete
- I2 – installation in water-filled drill holes (not sea water) and use in service in dry or wet concrete

### Installation:

- Hole drilling by hammer or compressed air drill mode.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.

### Installation direction:

- D3 - Downward and horizontal and upwards (e.g. overhead) installation.

**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**


**Intended use**  
Specifications

**Annex B 1**

**Table B1: Installation parameters for threaded rod**

Anchor size		M 8	M 10	M 12	M 16	M 20	M 24
Nominal drill hole diameter	$d_0$ [mm] =	10	12	14	18	24	28
Effective anchorage depth	$h_{ef,min}$ [mm] =	60	60	70	80	90	96
	$h_{ef,max}$ [mm] =	160	200	240	320	400	480
Diameter of clearance hole in the fixture	$d_f$ [mm] ≤	9	12	14	18	22	26
Maximum torque moment	$T_{inst}$ [Nm] ≤	10	20	40	80	120	160
Thickness of fixture	$t_{fix,min}$ [mm] >	0					
	$t_{fix,max}$ [mm] <	1500					
Minimum thickness of member	$h_{min}$ [mm]	$h_{ef} + 30 \text{ mm}$ $\geq 100 \text{ mm}$			$h_{ef} + 2d_0$		
Minimum spacing	$s_{min}$ [mm]	40	50	60	80	100	120
Minimum edge distance	$c_{min}$ [mm]	40	50	60	80	100	120

**Steel brush C1**



**Table B2: Parameter cleaning and setting tools**

Threaded Rod	$d_0$ Drill bit - Ø	$d_b$ Brush - Ø	$d_{b,min}$ min. Brush - Ø
(mm)	(mm)	(mm)	(mm)
M8	10	C1-10	12
M10	12	C1-12	14
M12	14	C1-14	16
M16	18	C1-18	20
M20	24	C1-24	26
M24	28	C1-28	30



**Hand pump (volume 750 ml)**

Drill bit diameter ( $d_0$ ): 10 mm to 20 mm  
and anchorage depth up to 240 mm



**Recommended compressed air tool (min 6 bar)**

All applications


#### **RESINA POLIESTER SIN ESTIRENO LUSAN for concrete POLIS, POLISB, POLIST, POLISE**

##### **Intended use**


Installation parameters  
Cleaning and setting tools

##### **Annex B 2**

## Installation instructions



1. Drill with hammer drill a hole into the base material to the size and embedment depth required by the selected anchor (Table B1). In case of aborted drill hole: the drill hole shall be filled with mortar.




- Attention! Standing water in the bore hole must be removed before cleaning.**
- 2a. Starting from the bottom or back of the bore hole, blow the hole clean with compressed air (min. 6 bar) or a hand pump (Annex B2) a minimum of four times. If the bore hole ground is not reached an extension shall be used.

or




The hand-pump can be used for anchor sizes up to bore hole diameter 20 mm.

For bore holes larger than 20 mm or deeper 240 mm, compressed air (min. 6 bar) **must** be used.



- 2b. Check brush diameter (Table B2) and attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized wire brush >  $d_{b,min}$  (Table B2) a minimum of four times.  
If the bore hole ground is not reached with the brush, a brush extension shall be used (Table B2).



- 2c. Finally blow the hole clean again with compressed air (min. 6 bar) or a hand pump (Annex B2) a minimum of four times. If the bore hole ground is not reached an extension shall be used.


The hand-pump can be used for anchor sizes up to bore hole diameter 20 mm.

For bore holes larger than 20 mm or deeper 240 mm, compressed air (min. 6 bar) **must** be used.

or




**After cleaning, the bore hole has to be protected against re-contamination in an appropriate way, until dispensing the mortar in the bore hole. If necessary, the cleaning repeated has to be directly before dispensing the mortar.**  
**In-flowing water must not contaminate the bore hole again**




3. Attach a supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. Cut off the foil tube clip before use.

For every working interruption longer than the recommended working time (Table B3) as well as for new cartridges, a new static-mixer shall be used.



4. Prior to inserting the anchor rod into the filled bore hole, the position of the embedment depth shall be marked on the anchor rods.




5. Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey or blue (POLISB) colour. For foil tube cartridges it must be discarded a minimum of six full strokes.

## RESINA POLIESTER SIN ESTIRENO LUSAN for concrete POLIS, POLISB, POLIST, POLISE


Intended use  
Installation instructions

Annex B 3

## Installation instructions (continuation)




**6.** Starting from the bottom or back of the cleaned anchor hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid creating air pockets. If the bottom or back of the anchor hole is not reached, an appropriate extension nozzle must be used. Observe the gel-/ working times given in Table B3.




**7.** Push the threaded rod into the anchor hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached.


The anchor should be free of dirt, grease, oil or other foreign material.



**8.** Be sure that the anchor is fully seated at the bottom of the hole and that excess mortar is visible at the top of the hole. If these requirements are not maintained, the application has to be renewed. For overhead application the anchor rod should be fixed (e.g. wedges).



**9.** Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B3).



**10.** After full curing, the add-on part can be installed with the max. torque (Table B1) by using a calibrated torque wrench.

**Table B3: Minimum curing time**

Concrete temperature	POLIST		POLIS, POLISB <sup>1)</sup>		POLISE	
	Max. working time	Min. curing time	Max. working time	Min. curing time	Max. working time	Min. curing time
-10 to -6 °C					60 min	4 h
-5 to -1 °C			90 min	6 h	45 min	2 h
0 to +4 °C			45 min	3 h	25 min	80 min
+5 to +9 °C			25 min	2 h	10 min	45 min
+10 to +14 °C	30 min	5 h	20 min	100 min	4 min	25 min
+15 to +19 °C	20 min	210 min	15 min	80 min	3 min	20 min
+20 to +29 °C	15 min	145 min	6 min	45 min	2 min	15 min
+30 to +34 °C	10 min	80 min	4 min	25 min		
+35 to +39 °C	6 min	45 min	2 min	20 min		
+40 to +44 °C	4 min	25 min				
+45 °C	2 min	20 min				
Cartridge temperature	+5°C to +45°C		+5°C to +40°C		0°C to +30°C	

<sup>1)</sup> The POLISB injection mortar has a curing time proof by changing the color from blue to gray after curing minimum time. The curing time proof is only valid for the standard version of the mortar.

**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

Intended use  
Installation instructions (continuation)  
Curing time

**Annex B 4**

**Table C1: Characteristic values for steel tension resistance and steel shear resistance of threaded rods**

Size			M 8	M 10	M 12	M 16	M 20	M24	
Cross section area	A <sub>s</sub>	[mm <sup>2</sup> ]	36,6	58	84,3	157	245	353	
<b>Characteristic tension resistance, Steel failure <sup>1)</sup></b>									
Steel, Property class 4.6 and 4.8	N <sub>Rk,s</sub>	[kN]	15 (13)	23 (21)	34	63	98	141	
Steel, Property class 5.6 and 5.8	N <sub>Rk,s</sub>	[kN]	18 (17)	29 (27)	42	78	122	176	
Steel, Property class 8.8	N <sub>Rk,s</sub>	[kN]	29 (27)	46 (43)	67	125	196	282	
Stainless steel A2, A4 and HCR, Property class 50	N <sub>Rk,s</sub>	[kN]	18	29	42	79	123	177	
Stainless steel A2, A4 and HCR, Property class 70	N <sub>Rk,s</sub>	[kN]	26	41	59	110	171	247	
Stainless steel A4 and HCR, Property class 80	N <sub>Rk,s</sub>	[kN]	29	46	67	126	196	282	
<b>Characteristic tension resistance, Partial safety factor <sup>2)</sup></b>									
Steel, Property class 4.6	γ <sub>Ms,N</sub>	[ - ]				2,0			
Steel, Property class 4.8	γ <sub>Ms,N</sub>	[ - ]				1,5			
Steel, Property class 5.6	γ <sub>Ms,N</sub>	[ - ]				2,0			
Steel, Property class 5.8	γ <sub>Ms,N</sub>	[ - ]				1,5			
Steel, Property class 8.8	γ <sub>Ms,N</sub>	[ - ]				1,5			
Stainless steel A2, A4 and HCR, Property class 50	γ <sub>Ms,N</sub>	[ - ]				2,86			
Stainless steel A2, A4 and HCR, Property class 70	γ <sub>Ms,N</sub>	[ - ]				1,87			
Stainless steel A4 and HCR, Property class 80	γ <sub>Ms,N</sub>	[ - ]				1,6			
<b>Characteristic shear resistance, Steel failure <sup>1)</sup></b>									
Without lever arm	Steel, Property class 4.6 and 4.8	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	9 (8)	14 (13)	20	38	59	85
	Steel, Property class 5.6 and 5.8	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	9 (8)	15 (13)	21	39	61	88
	Steel, Property class 8.8	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	15 (13)	23 (21)	34	63	98	141
	Stainless steel A2, A4 and HCR, Property class 50	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	9	15	21	39	61	88
	Stainless steel A2, A4 and HCR, Property class 70	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	13	20	30	55	86	124
	Stainless steel A4 and HCR, Property class 80	V <sup>0</sup> <sub>Rk,s</sub>	[kN]	15	23	34	63	98	141
With lever arm	Steel, Property class 4.6 and 4.8	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	15 (13)	30 (27)	52	133	260	449
	Steel, Property class 5.6 and 5.8	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	19 (16)	37 (33)	65	166	324	560
	Steel, Property class 8.8	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	30 (26)	60 (53)	105	266	519	896
	Stainless steel A2, A4 and HCR, Property class 50	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	19	37	66	167	325	561
	Stainless steel A2, A4 and HCR, Property class 70	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	26	52	92	232	454	784
	Stainless steel A4 and HCR, Property class 80	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	30	59	105	266	519	896
<b>Characteristic shear resistance, Partial safety factor <sup>2)</sup></b>									
Steel, Property class 4.6	γ <sub>Ms,V</sub>	[ - ]				1,67			
Steel, Property class 4.8	γ <sub>Ms,V</sub>	[ - ]				1,25			
Steel, Property class 5.6	γ <sub>Ms,V</sub>	[ - ]				1,67			
Steel, Property class 5.8	γ <sub>Ms,V</sub>	[ - ]				1,25			
Steel, Property class 8.8	γ <sub>Ms,V</sub>	[ - ]				1,25			
Stainless steel A2, A4 and HCR, Property class 50 50	γ <sub>Ms,V</sub>	[ - ]				2,38			
Stainless steel A2, A4 and HCR, Property class 50 70	γ <sub>Ms,V</sub>	[ - ]				1,56			
Stainless steel A4 and HCR, Property class 80	γ <sub>Ms,V</sub>	[ - ]				1,33			
<sup>1)</sup> Values are only valid for the given stress area A <sub>s</sub> . Values in brackets are valid for undersized threaded rods with smaller stress area A <sub>s</sub> for hot dipped threaded rods galvanized according to EN ISO 10684:2004+AC:2009.									
<sup>2)</sup> in absence of national regulation									
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for concrete POLIS, POLISB, POLIST, POLISE</b>							<b>Annex C 1</b>		
<b>Performances</b> Characteristic values for steel tension resistance and steel shear resistance of threaded rods									

**Table C2: Characteristic values under tension loads in uncracked concrete**

Anchor size threaded rod			M 8	M 10	M 12	M 16	M 20	M24	
<b>Steel failure</b>									
Characteristic tension resistance		N <sub>Rk,s</sub>	[kN]	A <sub>s</sub> • f <sub>uk</sub> (or see Table C1)					
Partial factor		γ <sub>Ms,N</sub>	[-]	see Table C1					
<b>Combined pull-out and concrete cone failure</b>									
Characteristic bond resistance in uncracked concrete C20/25									
Temperature range I: 40°C/24°C	dry and wet concrete	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	8,5	8,0	8,0	8,0	8,0	8,0
	flooded bore hole	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	8,5	8,0	8,0	8,0	8,0	8,0
Temperature range II: 80°C/50°C	dry and wet concrete	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	6,5	6,0	6,0	6,0	6,0	6,0
	flooded bore hole	τ <sub>Rk,ucr</sub>	[N/mm <sup>2</sup> ]	6,5	6,0	6,0	6,0	6,0	6,0
Increasing factors for concrete ψ <sub>c</sub>		C25/30		1,04					
		C30/37		1,08					
		C35/45		1,13					
		C40/50		1,15					
		C45/55		1,17					
		C50/60		1,19					
<b>Concrete cone failure</b>									
Factor		k <sub>ucr,N</sub>	[-]	11,0					
Edge distance		c <sub>cr,N</sub>	[mm]	1,5 h <sub>ef</sub>					
Axial distance		s <sub>cr,N</sub>	[mm]	2 c <sub>cr,N</sub>					
<b>Splitting failure</b>									
Edge distance	h/h <sub>ef</sub> ≥ 2,0	c <sub>cr,sp</sub>	[mm]	1,0 h <sub>ef</sub>					
	2,0 > h/h <sub>ef</sub> > 1,3			2 · h <sub>ef</sub> $\left( 2,5 - \frac{h}{h_{ef}} \right)$					
	h/h <sub>ef</sub> ≤ 1,3			2,4 h <sub>ef</sub>					
Axial distance		s <sub>cr,sp</sub>	[mm]	2 c <sub>cr,sp</sub>					
<b>Installation factor</b>									
for dry and wet concrete		γ <sub>inst</sub>	[-]	1,2					
for flooded bore hole		γ <sub>inst</sub>	[-]	1,2					
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for concrete POLIS, POLISB, POLIST, POLISE</b>									<b>Annex C 2</b>
<b>Performances</b> Characteristic values under tension loads in uncracked concrete									

**Table C3: Characteristic values under shear loads in uncracked concrete**

Anchor size threaded rod		M 8	M 10	M 12	M 16	M 20	M24				
<b>Steel failure without lever arm</b>											
Characteristic shear resistance Steel, strength class 4.6 and 4.8	$V_{Rk,s}^0$	[kN]	$0,6 \cdot A_s \cdot f_{uk}$ (or see Table C1)								
Characteristic shear resistance Steel, strength class 5.6, 5.8 and 8.8 Stainless Steel A2, A4 and HCR, all classes	$V_{Rk,s}^0$	[kN]	$0,5 \cdot A_s \cdot f_{uk}$ (or see Table C1)								
Partial factor	$\gamma_{Ms,V}$	[·]	see Table C1								
Ductility factor	$k_7$	[·]	1,0								
<b>Steel failure with lever arm</b>											
Characteristic bending moment	$M_{Rk,s}^0$	[Nm]	$1,2 \cdot W_{el} \cdot f_{uk}$ (or see Table C1)								
Partial factor	$\gamma_{Ms,V}$	[·]	see Table C1								
<b>Concrete pry-out failure</b>											
Factor	$k_8$	[·]	2,0								
Installation factor	$\gamma_{inst}$	[·]	1,0								
<b>Concrete edge failure</b>											
Effective length of fastener	$l_f$	[mm]	$l_f = \min(h_{ef}, 12 d_{nom})$								
Outside diameter of fastener	$d_{nom}$	[mm]	8	10	12	16	20				
Installation factor	$\gamma_{inst}$	[·]	1,0								
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for concrete POLIS, POLISB, POLIST, POLISE</b>											
<b>Performances</b> Characteristic values under shear loads in uncracked concrete											
<b>Annex C 3</b>											

**Table C4: Displacement under tension load<sup>1)</sup>**

Anchor size threaded rod		M 8	M 10	M 12	M 16	M 20	M24	
<b>Uncracked concrete C20/25</b>								
Temperature range I: 40°C/24°C	δ <sub>N0</sub> -factor	[mm/(N/mm <sup>2</sup> )]	0,03	0,04	0,05	0,07	0,08	0,10
	δ <sub>N∞</sub> -factor	[mm/(N/mm <sup>2</sup> )]	0,07	0,08	0,08	0,08	0,08	0,10
Temperature range II: 80°C/50°C	δ <sub>N0</sub> -factor	[mm/(N/mm <sup>2</sup> )]	0,02	0,03	0,03	0,04	0,04	0,05
	δ <sub>N∞</sub> -factor	[mm/(N/mm <sup>2</sup> )]	0,15	0,17	0,17	0,17	0,17	0,17

<sup>1)</sup> Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau;$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

**Table C5: Displacement under shear load<sup>1)</sup>**

Anchor size threaded rod		M 8	M 10	M 12	M 16	M 20	M24
<b>For uncracked concrete C20/25</b>							
All temperature ranges	δ <sub>V0</sub> -factor	[mm/kN]	0,02	0,02	0,01	0,01	0,01
	δ <sub>V∞</sub> -factor	[mm/kN]	0,03	0,02	0,02	0,01	0,01

<sup>1)</sup> Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V;$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V;$$

**RESINA POLIESTER SIN ESTIRENO LUSAN for concrete  
POLIS, POLISB, POLIST, POLISE**

**Performances**  
Displacement

**Annex C 4**



Technical and Test Institute  
for Construction Prague  
Prosecká 811/76a  
190 00 Prague  
Czech Republic  
eota@tzus.cz



www.eota.eu

## European Technical Assessment

**ETA 21/0289  
of 12/04/2021**

(English language translation, the original version in Czech language)

**Technical Assessment Body issuing the ETA:** Technical and Test Institute for Construction Prague

**Trade name of the construction product**

RESINA POLIESTER SIN ESTIRENO LUSAN

**Product family to which the construction product belongs**

Product area code: 33  
Injection anchors for use in masonry

**Manufacturer**

LUSAN fijaciones y anclajes  
Molinos 20  
29491 Algatocín Málaga  
Spain

**Manufacturing plant(s)**

Plant 1

**This European Technical Assessment contains**

56 pages including 53 Annexes which form an integral part of this assessment.

**This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of**

EAD 330076-00-0604 Metal injection anchors for use in masonry

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such.

## **1. Technical description of the product**

The RESINA POLIESTER SIN ESTIRENO LUSAN POLIS, POLISB, POLIST, POLISE for masonry is bonded anchor consisting of a cartridge with injection mortar, a steel element and a plastic sleeve. The steel elements are the commercial threaded rods with hexagon nut and washer. The steel elements are made of galvanized or zinc plated steel, stainless or high corrosion resistance steel.

The anchor is placed into a drilled hole filled with injection mortar. The steel element is anchored via the bond between metal part, injection mortar and masonry.

The illustration and the description of the product are given in Annex A.

## **2. Specification of the intended use in accordance with the applicable EAD**

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The provisions made in this European Technical Assessment are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the products in relation to the expected economically reasonable working life of the works.

## **3. Performance of the product and references to the methods used for its assessment**

### **3.1 Mechanical resistance and stability (BWR 1)**

<b>Essential characteristic</b>	<b>Performance</b>
Characteristic values for resistance	Annex C6 to C40
Displacements	Annex C5 to C39
Durability	Annex B1

### **3.2 Safety in case of fire (BWR 2)**

<b>Essential characteristic</b>	<b>Performance</b>
Reaction to fire	Anchorages satisfy requirements for Class A1

### **3.3 Hygiene, health and environment (BWR 3)**

No performance determined.

### **3.4 General aspects relating to fitness for use**

Durability and serviceability are only ensured if the specifications of intended use according to Annex B 1 are taken into account.

## **4. Assessment and verification of constancy of performance (AVCP) system applied with reference to its legal base**

According to the Decision 97/177/EC of the European Commission<sup>1</sup> the system of assessment verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table applies.

<b>Product</b>	<b>Intended use</b>	<b>Level or class</b>	<b>System</b>
Injection anchors for use in masonry	For fixing and/or supporting to masonry, structural elements (which contributes to the stability of the construction works) or heavy units	-	1

<sup>1</sup> Official Journal of the European Communities L 073 of 14.03.1997

**5. Technical details necessary for the implementation of the AVCP system, as provided in the applicable EAD**

**5.1 Tasks of the manufacturer**

The manufacturer may only use raw materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the control plan which is a part of the technical documentation of this European Technical Assessment. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Technical and Test Institute for Construction Prague<sup>2</sup> The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

**5.2 Tasks of the notified bodies**

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The notified certification body involved by the manufacturer shall issue a certificate of constancy of performance of the product stating the conformity with the provisions of this European Technical Assessment.

In cases where the provisions of the European Technical Assessment and its control plan are no longer fulfilled the notified body shall withdraw the certificate of constancy of performance and inform Technical and Test Institute for Construction Prague without delay.

Issued in Prague on 12.04.2020


By

**Ing. Mária Schaan**  
Head of the TAB


---

<sup>2</sup> The control plan is a confidential part of the documentation of the European technical assessment, but not published together with the ETA and only handed over to the approved body involved in the procedure of AVCP.


### Installation in hollow brick; threaded rod with sleeve



### Installation in solid brick; threaded rod with sleeve



### Installation in solid brick; threaded rod without sleeve



$d_0$  = nominal drill hole diameter  
 $t_{\text{fix}}$  = thickness of fixture  
 $T_{\text{inst},\text{max}}$  = max installation torque moment

$h$  = thickness of member  
 $h_0$  = depth of drill hole at shoulder  
 $h_{\text{ef}}$  = effective anchorage depth  
 $h_{\text{nom}}$  = overall embedment depth


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Installed condition


**Annex A 1**

## **Cartridge: POLIS, POLISB, POLIST, POLISE**


**150 ml, 280 ml, 300 ml up to 333 ml, 380 ml up to 420 ml cartridge (Type: coaxial)**



**235 ml, 345 ml up to 360 ml, 825 ml cartridge (Type: "side-by-side")**



**165 ml and 300 ml cartridge (Type: "foil tube")**



## **Static mixer**

**SM 14W**




**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Injection system

**Annex A 2**

### Threaded rod M8 / M10 / M12 / M16



Commercial standard threaded rod with:

- Materials, dimensions and mechanical properties acc. Table A1
- Inspection certificate 3.1 acc. to EN 10204:2004. The document shall be stored.
- Marking of embedment depth

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Product description**  
Threaded rod

**Annex A 3**

**Table A1: Materials**

Part	Designation	Material	
<b>Steel, zinc plated (Steel acc. to EN 10087:1998 or EN 10263:2001)</b>			
zinc plated ≥ 5 µm acc. to EN ISO 4042:1999 or hot-dip galvanised ≥ 40 µm acc. to EN ISO 1461:2009 and EN ISO 10684:2004+AC:2009 or sherardized ≥ 40 µm acc. to EN ISO 17668:2016			
1	Anchor rod	4.6 $f_{uk}=400 \text{ N/mm}^2; f_{yk}=240 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$	
		4.8 $f_{uk}=400 \text{ N/mm}^2; f_{yk}=320 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$	
		5.6 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=300 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$	
		5.8 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=400 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$	
		8.8 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=640 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$	
2	Hexagon nut	4 for anchor rod class 4.6 or 4.8	
		5 for anchor rod class 5.6 or 5.8	
		8 for anchor rod class 8.8	
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	Steel, zinc plated, hot-dip galvanised or sherardized	
<b>Stainless steel A2 (Material 1.4301 / 1.4303 / 1.4307 / 1.4567 or 1.4541, acc. to EN 10088-1:2014) and Stainless steel A4 (Material 1.4401 / 1.4404 / 1.4571 / 1.4362 or 1.4578, acc. to EN 10088-1:2014)</b>			
1	Anchor rod <sup>1)</sup>	Property class acc. to EN ISO 3506-1:2009	50 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=210 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
			70 $f_{uk}=700 \text{ N/mm}^2; f_{yk}=450 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
			80 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=600 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
2	Hexagon nut <sup>1)</sup>	Property class acc. to EN ISO 3506-1:2009	50 for anchor rod class 50
			70 for anchor rod class 70
			80 for anchor rod class 80
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	A2: Material 1.4301, 1.4303 / 1.4307 / 1.4567 or 1.4541, EN 10088-1:2014 A4: Material 1.4401, 1.4404 / 1.4571 / 1.4362 or 1.4578, EN 10088-1:2014	
<b>High corrosion resistance steel (Material 1.4529 or 1.4565, acc. to EN 10088-1: 2014)</b>			
1	Anchor rod	Property class acc. to EN ISO 3506-1:2009	50 $f_{uk}=500 \text{ N/mm}^2; f_{yk}=210 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
			70 $f_{uk}=700 \text{ N/mm}^2; f_{yk}=450 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
			80 $f_{uk}=800 \text{ N/mm}^2; f_{yk}=600 \text{ N/mm}^2; A_5 > 8\% \text{ fracture elongation}$
2	Hexagon nut	Property class acc. to EN ISO 3506-1:2009	50 for anchor rod class 50
			70 for anchor rod class 70
			80 for anchor rod class 80
3	Washer, (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 oder EN ISO 7094:2000)	Material 1.4529 or 1.4565, acc. to EN 10088-1: 2014	

<sup>1)</sup> Strength class 80 only for stainless steel A4

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Product description**

Materials

**Annex A 4**


### Sleeve (Plastic)

SH 12x80

SH 16x85

SH 20x85

$$l_s = h_{ef} = h_{nom}$$




SH 16x130

SH 20x130

SH 20x200

$$l_s = h_{ef} = h_{nom}$$




SH 16x130/330

$$l_s$$

$$t_{fix}$$

$$h_{ef} = h_{nom}$$

$$d_s$$



**Table A2: Sleeve sizes (mm)**

Sleeve			
Size	$d_s$ [mm]	$l_s$ [mm]	$h_{ef} = h_{nom}$ [mm]
SH12x80	12	80	80
SH16x85	16	85	85
SH16x130	16	130	130
SH16x130/330	16	330	130
SH20x85	20	85	85
SH20x130	20	130	130
SH20x200	20	200	200

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Product description**

Sleeves

**Annex A 5**

## Specifications of intended use

### Anchorage subject to:

- Static and quasi-static loads

### Base materials

- Autoclaved Aerated Concrete (Masonry group d) to Annex B2.
- Solid brick masonry (Masonry group b), according to Annex B2 to B4.
- Hollow brick masonry (Masonry group c), according to Annex B2 to B4.
- Mortar strength class of the masonry M2,5 at minimum according to EN 998-2:2010.
- Joints of the masonry must be visible and filled with mortar.
- For other bricks in solid masonry and in hollow or perforated masonry, the characteristic resistance of the anchor may be determined by job site tests according to EOTA Technical Report TR 053 under consideration of the  $\beta$ -factor to Annex C1, Table C1.

Note: The characteristic resistances are also valid for larger brick sizes and larger compressive strength of the masonry unit.

### Temperature range:

- $T_a$ : -40°C to +40°C (max. short. term temperature +40°C and max. long term temperature +24°C)
- $T_b$ : -40°C to +80°C (max. short. term temperature +80°C and max. long term temperature +50°C)

### Use conditions (Environmental conditions)

- Dry and wet structures (regarding injection mortar).  
(X1) Structures subject to dry internal conditions (zinc coated steel, stainless steel A2 resp. A4 or high corrosion resistant steel).
- (X2) Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel A4 or high corrosion resistant steel).
- (X3) Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (high corrosion resistant steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

### Use conditions in respect of installation and use:

- Category d/d: Installation and use in dry masonry
- Category w/w: Installation and use in wet masonry (incl. w/d installation in wet masonry and use in dry masonry)

### Design:


- Verifiable calculation notes and drawings are prepared taking account the relevant masonry in the region of the anchorage, the loads to be transmitted and their transmission to the supports of the structure. The position of the anchor is indicated on the design drawings.
- The anchorage are designed in accordance with the EOTA Technical Report TR 054, Design method A under the responsibility of an engineer experienced in anchorages and masonry work.

### Installation:



- Dry or wet structures
- Anchor Installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.

<b>RESINA POLIESTER SIN ESTIRENO LUSAN for masonry POLIS, POLISB, POLIST, POLISE</b>	<b>Annex B 1</b>
<b>Intended use</b> Specifications	

**Table B1: Overview brick types and properties with corresponding fastening elements  
(Anchors and Sleeves)**

Brick-Nr.	Brick type	picture	Brick size Length x width x height	Compressive strength	Bulk density	Sleeve - Anchor type	Annex
			[mm]	[N/mm <sup>2</sup> ]	[kg/dm <sup>3</sup> ]		
<b>Autoclaved aerated concrete units according EN 771-4</b>							
1	Autoclaved Aerated Concrete AAC2		599 x 375 x 249	2	0,35	M8 / M10 / M12 / M16	C4 / C5
2	Autoclaved Aerated Concrete AAC4		499 x 375 x 249	4	0,5	M8 / M10 / M12 / M16	C6 / C7
3	Autoclaved Aerated Concrete AAC6		499 x 240 x 249	6	0,6	M8 / M10 / M12 / M16	C8 / C9
<b>Calcium silicate masonry units according EN 771-2</b>							
4	Calcium silicate solid brick KS-NF		240 x 115 x 71	10 20 27	2,0	M8 / M10 / M12 / M16 SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C10 / C11
5	Calcium silicate hollow brick KS L-3DF		240 x 175 x 113	8 12 14	1,4	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C12 / C13
6	Calcium silicate hollow brick KS L-12DF		498 x 175 x 238	10 12 16	1,4	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x130 – M12 / M16	C14 / C15
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for masonry POLIS, POLISB, POLIST, POLISE</b>							
<b>Intended use</b> Brick types and properties with corresponding fastening elements						<b>Annex B 2</b>	

**Table B1: Overview brick types and properties with corresponding fastening elements  
(Anchors and Sleeves)**

Brick-Nr.	Brick type	picture	Brick size Length x width x height	Compressive strength	Bulk density	Sleeve - Anchor type	Annex
			[mm]	[N/mm <sup>2</sup> ]	[kg/dm <sup>3</sup> ]		
<b>Clay masonry units according EN 771-1</b>							
7	Clay solid brick Mz – DF		240 x 115 x 55	10 20 28	1,64	M8 / M10 / M12 / M16 SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C16 / C17
8	Clay hollow brick HLz-16DF		497 x 240 x 238	6 9 12 14	0,83	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C18 / C19
9	Clay hollow brick Porotherm Homebrick		500 x 200 x 299	6 8 10	0,68	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C20 / C21
10	Clay hollow brick BGV Thermo		500 x 200 x 314	4 6 10	0,62	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C22 / C23
11	Clay hollow brick Calibric Th		500 x 200 x 314	6 9 12	0,62	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C24 / C25
12	Clay hollow brick Urbanbrick		560 x 200 x 274	6 9	0,74	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C26 / C27
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for masonry POLIS, POLISB, POLIST, POLISE</b>						<b>Annex B 3</b>	
<b>Intended use</b> Brick types and properties with corresponding fastening elements							

**Table B1: Overview brick types and properties with corresponding fastening elements  
(Anchors and Sleeves)**

Brick-Nr.	Brick type	picture	Brick size Length x width x height	Compressive strength	Bulk density	Sleeve - Anchor type	Annex
			[mm]	[N/mm <sup>2</sup> ]	[kg/dm <sup>3</sup> ]		
<b>Clay masonry units according EN 771-1</b>							
13	Clay hollow brick Blocchi Leggeri		250 x 120 x 250	4 6 8	0,55	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C28 / C29
14	Clay hollow brick Doppio Uni		250 x 120 x 120	10 16 20 28	0,92	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16 SH 20x200 – M12 / M16	C30 / C31
<b>Light weight concrete according EN 771-3</b>							
15	Hollow light weight concrete Bloc creux B40		494 x 200 x 190	4	0,80	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C32 / C33
16	Solid light weight concrete		300 x 123 x 248	2	0,63	M8 / M10 / M12 / M16	C34 / C35
17	Hollow light weight Leca Lex harkko RUH- 200		498 x 200 x 195	2,7	0,62	SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C36 / C37
18	Solid light weight Leca Lex RUH-200 Kulma		498 x 200 x 195	3	0,62	M8 / M10 / M12 / M16 SH 12x80 – M8 SH 16x85 – M8 / M10 SH 16x130 – M8 / M10 SH 16x130/330 - M8 / M10 SH 20x85 – M12 / M16 SH 20x130 – M12 / M16	C38 / C39
<b>RESINA POLIESTER SIN ESTIRENO LUSAN for masonry POLIS, POLISB, POLIST, POLISE</b>							
<b>Intended use</b> Brick types and properties with corresponding fastening elements						<b>Annex B 4</b>	

### Installation: Steel brush C1



**Table B2: Installation parameters in Autoclaved Aerated Concrete AAC and solid masonry (without sleeve)**

Threaded rod			M8	M10	M12	M16
Nominal drill hole diameter	$d_0$	[mm]	10	12	14	18
Drill hole depth	$h_0$	[mm]	80	90	100	100
Effective anchorage depth	$h_{\text{ef}} = h_{\text{nom}}$	[mm]	80	90	100	100
Minimum wall thickness	$h_{\text{min}}$	[mm]	$h_{\text{ef}} + 30$			
Diameter of clearance hole in the fixture	$d_f \leq$	[mm]	9	12	14	18
Diameter of Steel brush	$d_b \geq$	[mm]	C1-10 12	C1-12 14	C1-14 16	C1-18 20
Minimum diameter of steel brush	$d_{b,\text{min}}$	[mm]	10,5	12,5	14,5	18,5
Max torque moment	$T_{\text{inst}}$	[Nm]	See parameters of brick Annex C4 to Annex C39			

**Table B3: Installation parameters in solid and hollow masonry (with sleeve)**

Threaded rod		M8	M8 / M10			M12 / M16		
Sleeve	[mm]	SH12x80	SH16x85	SH16x130	SH16x130/ 330	SH20x85	SH20x130	SH20x200
Nominal drill hole diameter	$d_0$	[mm]	12	16	16	16	20	20
Drill hole depth	$h_0$	[mm]	85	90	135	$135 + t_{\text{fix}}^1)$	90	135
Effective anchorage depth	$h_{\text{ef}} = h_{\text{nom}}$	[mm]	80	85	130	130	85	130
Minimum wall thickness	$h_{\text{min}}$	[mm]	115	115	195	195	115	195
Diameter of clearance hole in the fixture	$d_f \leq$	[mm]	9	9 (M8) / 12 (M10)			14 (M12) / 18 (M16)	
Diameter of brush	$d_b \geq$	[mm]	C1-12 14	C1-16 18			C1-20 22	
Minimum diameter of brush	$d_{b,\text{min}}$	[mm]	12,5	16,5			20,5	
Max torque moment	$T_{\text{inst}}$	[Nm]	See parameters of brick Annex C4 to Annex C39					

<sup>1)</sup>  $t_{\text{fix}} < 200$  mm

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Intended use**  
Installation parameters and cleaning brush

**Annex B 5**

**Table B4: Maximum working time and minimum curing time**

Temperature in the base material	POLIST		POLIS, POLISB <sup>1)</sup>		POLISE	
	Max. working time	Min. curing time	Max. working time	Min. curing time	Max. working time	Min. curing time
0°C to +4°C			45 min	3 h	25 min	80 min
+5°C to +9°C			25 min	2 h	10 min	45 min
+10°C to +14°C	30 min	5 h	20 min	100 min	4 min	25 min
+15°C to +19°C	20 min	210 min	15 min	80 min	3 min	20 min
+20°C to +29°C	15 min	145 min	6 min	45 min	2 min	15 min
+30°C to +34°C	10 min	80 min	4 min	25 min		
+35°C to +39°C	6 min	45 min	2 min	20 min		
+40°C to +44°C	4 min	25 min				
+45°C	2 min	20 min				
Cartridge temperature	+5°C to +45°C		+5°C to +40°C		-5°C to +30°C	

<sup>1)</sup> The POLISB injection mortar has a curing time proof by changing the color from blue to gray after curing minimum time. The curing time proof is only valid for the standard version of the mortar.



**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Intended use**  
Working and curing time

**Annex B 6**



## Installation instructions

### Preparation of cartridge




1. Remove the cap and attach the supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. In case of a foil tube cartridge, cut off the clip before use. For every working interruption longer than the recommended working time (Table B4) as well as for new cartridges, a new static-mixer shall be used.
2. Prior to dispensing into the anchor hole, squeeze out separately a minimum of three full strokes, for foil tube cartridges six full strokes, and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey or blue (POLISB) colour.


### Installation in solid masonry (without sleeve)



3. Holes to be drilled perpendicular to the surface of the base material by using a hard-metal tipped hammer drill bit. Drill a hole, with drill method according to Annex C4 – C39, into the base material, with nominal drill hole diameter and bore hole depth acc. to the size and embedment depth required by the selected anchor. In case of aborted drill hole the drill hole shall be filled with mortar.




4. Blow out from the bottom of the drill hole two times. Attach the appropriate sized brush ( $> d_{b,min}$  Table B2 or B3) to a drilling machine or a battery screwdriver, brush the hole clean two times, and finally blow out the hole again two times.



5. Starting from the bottom or back of the cleaned anchor hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid creating air pockets.


Observe the gel-/ working times given in Table B4.




6. The position of the embedment depth shall be marked on the threaded rod. Push the threaded rod into the drill hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached. The anchor shall be free of dirt, grease, oil or other foreign material.



7. Be sure that the annular gap is fully filled with mortar. If no excess mortar is visible at the top of the hole, the application has to be renewed.



8. Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B4).



9. After full curing, the fixture can be installed with up to the max. torque (see parameters of brick Annex C5 to Annex C39) by using a calibrated torque wrench.

### RESINA POLIESTER SIN ESTIRENO LUSAN for masonry POLIS, POLISB, POLIST, POLISE


#### Intended use

Installation instruction Solid masonry and Autoclaved Aerated Concrete



#### Annex B 7

## Installation instructions (continuation)


### Installation in solid and hollow masonry (with sleeve)




3. Holes to be drilled perpendicular to the surface of the base material by using a hard-metal tipped hammer drill bit. Drill a hole, with drill method according to Annex C4 – C39, into the base material, with nominal drill hole diameter and drill hole depth acc. to the size and embedment depth required by the selected anchor. In case of aborted drill hole the drill hole shall be filled with mortar.



4. Blow out from the bottom of the drill hole two times. Attach the appropriate sized brush ( $> d_{b,min}$  Table B2 or B3) to a drilling machine or a battery screwdriver, brush the hole clean two times, and finally blow out the hole again two times.





5. Insert the sleeve flush with the surface of the masonry. Only use sleeves that have the right length. Never cut the sleeve except the sleeve 16x130/330. For installing the sleeve 16x130/330 measure the required length of sleeve, cut the sleeve from the top and set the cap on it before pushing it through the fixing element.




6. Starting from the bottom or back fill the sleeve with adhesive. For quantity of mortar attend cartridges label or installation instructions.


Observe the gel-/ working times given in Table B4.



7. The position of the embedment depth shall be marked on the threaded rod. Push the threaded rod into the drill hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached. The anchor shall be free of dirt, grease, oil or other foreign material.



8. Allow the adhesive to cure to the specified curing time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B4).



9. After full curing, the fixture can be installed with up to the max. torque (see parameters of brick Annex C5 to Annex C39) by using a calibrated torque wrench.

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Intended use**

Installation instructions (hollow brick) and Solid lightweight Concrete

**Annex B 8**

**Table C1:  $\beta$ -factors for job-site testing under tension loading**

Brick-Nr.	Installation & Use conditions	Anchor size	$\beta$ -factor	
			T <sub>a</sub> : 24°C / 40°C	T <sub>b</sub> : 50°C / 80°C
1-3	d/d	M8	0,82	0,70
		M10		
		M12	0,70	0,60
		M16		
	w/w	M8	0,82	0,70
		M10	0,63	0,54
		M12	0,48	0,41
		M16		
4-18	d/d w/d w/w	For all anchor	0,72	0,50

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performances**  
 $\beta$ -factors for job site testing under tension load

**Annex C 1**

**Table C2: Characteristic tension, shear resistance and bending moment of threaded rod**


<b>Size</b>		<b>M8</b>	<b>M10</b>	<b>M12</b>	<b>M16</b>
<b>Characteristic tension resistance</b>					
steel, property class 4.6 <sup>2)</sup>					
$N_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63
$\gamma_{Ms}^{1)}$	[-]		2,0		
$N_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63
$\gamma_{Ms}^{1)}$	[-]		1,5		
$N_{Rk,s}$	[kN]	18 (17)	29 (27)	42	79
$\gamma_{Ms}^{1)}$	[-]		2,0		
$N_{Rk,s}$	[kN]	18 (17)	29 (27)	42	79
$\gamma_{Ms}^{1)}$	[-]		1,5		
$N_{Rk,s}$	[kN]	29 (27)	46 (43)	67	126
$\gamma_{Ms}^{1)}$	[-]		1,5		
$N_{Rk,s}$	[kN]	26	41	59	110
$\gamma_{Ms}^{1)}$	[-]		1,87		
$N_{Rk,s}$	[kN]	29	46	67	126
$\gamma_{Ms}^{1)}$	[-]		1,6		
<b>Characteristic shear resistance</b>					
steel, property class 4.6 <sup>2)</sup>					
$V_{Rk,s}$	[kN]	7 (7)	12 (11)	17	31
$\gamma_{Ms}^{1)}$	[-]		1,67		
$V_{Rk,s}$	[kN]	7 (7)	12 (11)	17	31
$\gamma_{Ms}^{1)}$	[-]		1,25		
$V_{Rk,s}$	[kN]	9 (8)	15 (13)	21	39
$\gamma_{Ms}^{1)}$	[-]		1,67		
$V_{Rk,s}$	[kN]	9 (8)	15 (13)	21	39
$\gamma_{Ms}^{1)}$	[-]		1,25		
$V_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63
$\gamma_{Ms}^{1)}$	[-]		1,25		
$V_{Rk,s}$	[kN]	13	20	30	55
$\gamma_{Ms}^{1)}$	[-]		1,56		
$V_{Rk,s}$	[kN]	15	23	34	63
$\gamma_{Ms}^{1)}$	[-]		1,33		
<b>Characteristic bending moment</b>					
steel, property class 4.6 <sup>2)</sup>					
$M_{Rk,s}$	[Nm]	15 (13)	30 (27)	52	133
$\gamma_{Ms}^{1)}$	[-]		1,67		
$M_{Rk,s}$	[Nm]	15 (13)	30 (27)	52	133
$\gamma_{Ms}^{1)}$	[-]		1,25		
$M_{Rk,s}$	[Nm]	19 (16)	37 (33)	65	166
$\gamma_{Ms}^{1)}$	[-]		1,67		
$M_{Rk,s}$	[Nm]	19 (16)	37 (33)	65	166
$\gamma_{Ms}^{1)}$	[-]		1,25		
$M_{Rk,s}$	[Nm]	30 (26)	60 (53)	105	266
$\gamma_{Ms}^{1)}$	[-]		1,25		
$M_{Rk,s}$	[Nm]	26	52	92	232
$\gamma_{Ms}^{1)}$	[-]		1,56		
$M_{Rk,s}$	[Nm]	30	60	105	266
$\gamma_{Ms}^{1)}$	[-]		1,33		

<sup>1)</sup> In absence of national regulations<sup>2)</sup> Values in brackets valid for hot dipped galvanized undersized threaded rods with smaller stress area  $A_s$  according to EN ISO 10684:2004+AC:2009**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE****Performances**

Characteristic tension, shear resistance and bending moment of threaded rod

**Annex C 2**

## Spacing and edge distances



- $C_{cr}$  = Characteristic edge distance  
 $C_{min}$  = Minimum edge distance  
 $S_{cr}$  = Characteristic spacing  
 $S_{min}$  = Minimum spacing  
 $S_{cr\parallel}; (S_{min\parallel})$  = Characteristic (minimum) spacing for anchors placed parallel to bed joint  
 $S_{cr\perp}; (S_{min\perp})$  = Characteristic (minimum) spacing for anchors placed perpendicular to bed joint

Anchor position \ Load direction	Tension load	Shear load parallel to free edge	Shear load perpendicular to free edge
Anchors places parallel to bed joint $s_{cr,\parallel}; (s_{min,\parallel})$			
Anchors places perpendicular to bed joint $s_{cr,\perp}; (s_{min,\perp})$			

- $\alpha_{g,N,\parallel}$  = Group factor in case of tension load for anchors placed parallel to the bed joint  
 $\alpha_{g,V,\parallel}$  = Group factor in case of shear load for anchors placed parallel to the bed joint  
 $\alpha_{g,N,\perp}$  = Group factor in case of tension load for anchors placed perpendicular to the bed joint  
 $\alpha_{g,V,\perp}$  = Group factor in case of shear load for anchors placed perpendicular to the bed joint

Group of two anchors:  $N^g_{Rk} = \alpha_{g,N} * N_{Rk}$  and  $V^g_{Rk} = \alpha_{g,V} * V_{Rk}$   
 Group of four anchors:  $N^g_{Rk} = \alpha_{g,N,\parallel} * \alpha_{g,N,\perp} * N_{Rk}$  and  $V^g_{Rk} = \alpha_{g,V,\parallel} * \alpha_{g,V,\perp} * V_{Rk}$   
 ( $N_{Rk}$ :  $N_{Rk,b}$  or  $N_{Rk,b,j}$  for  $c_{cr}$ )  
 ( $V_{Rk}$ :  $V_{Rk,c}$ ;  $V_{Rk,c,j}$ ;  $V_{Rk,b}$  or  $V_{Rk,b,j}$  for  $c_{cr}$ )  
 (with the relevant  $\alpha_g$ )



**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry**  
**POLIS, POLISB, POLIST, POLISE**

**Performances**  
Edge distance and anchor spacing



**Annex C 3**

## Group factor, valid for all brick types



### Group factor for anchor group in case of tension loading

Configuration		with $c \geq$	with $s \geq$			
II: anchors placed parallel to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,N,II}$	[-]	2,0
⊥: anchors placed perpendicular to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,N,\perp}$		2,0

### Group factor for anchor group in case of shear loading parallel to free edge

Configuration		with $c \geq$	with $s \geq$			
II: anchors placed parallel to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,V,II}$	[-]	2,0
⊥: anchors placed perpendicular to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,V,\perp}$		2,0

### Group factor for anchor group in case of shear loading perpendicular to free edge

Configuration		with $c \geq$	with $s \geq$			
II: anchors placed parallel to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,V,II}$	[-]	2,0
⊥: anchors placed perpendicular to horizontal joint		$C_{cr}$	$S_{cr}$	$\alpha_{g,V,\perp}$		2,0

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performances**  
Group factor

**Annex C 4**

## Brick type: Autoclaved Aerated Concrete – AAC2

**Table C3: Description**

Brick type	Autoclaved Aerated Concrete AAC2	
Bulk density [kg/dm <sup>3</sup> ]	0,35	
Compressive strength [N/mm <sup>2</sup> ]	2	
Code	EN 771-4	
Producer (country code)	e.g. Ytong (CZ)	
Brick dimensions [mm]	599 x 375 x 249	
Drilling method	Rotary drilling	

**Table C4: Installation parameter (Edge and spacing distances)**

Anchor size	Effective anchorage depth	Edge distance	Spacing	Maximum installation torque
				$T_{inst,max}$
	$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min\ II} = S_{min\ \perp}$	[Nm]
<b>M8</b>	80	120	240	2
	<b>M10</b>	90	270	
	<b>M12</b>	100	300	
	<b>M16</b>	100	300	

**Table C5: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$\frac{N_{Rk}}{1,4 \cdot \gamma_M}$	0,29	0,58	$\frac{V_{Rk}}{1,4 \cdot \gamma_M}$	1,23	1,84
90		0,23	0,46		0,87	1,31
100		0,39	0,79		1,29	1,94

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC2**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 5**

**Brick type: Autoclaved Aerated Concrete AAC2**

**Table C6: Characteristic values of resistance under tension and shear loads**

Anchor size	Effective anchorage depth  h <sub>ef</sub> [mm]	Characteristic resistance				
		Use conditions				
		d/d		w/d w/w		d/d w/d w/w
		40°C / 24°C		80°C / 50°C		For all temperature range
		N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	V <sub>Rk,b</sub> <sup>2)</sup>
<b>Compressive strength f<sub>b</sub> ≥ 2 N/mm<sup>2</sup></b>		[kN]				
<b>M8</b>	80	0,9	0,9	0,9	0,9	1,5
<b>M10</b>	90	0,9	0,9	0,9	0,75	2,0
<b>M12</b>	100	1,5	1,5	1,2	0,9	2,5
<b>M16</b>	100	1,5	1,5	1,2	0,9	3,5

<sup>1)</sup> For design according TR 054: N<sub>Rk</sub> = N<sub>Rk,p</sub> = N<sub>Rk,b</sub>; N<sub>Rk,s</sub> according to Table C2 Annex C2; Calculation N<sub>Rk,pb</sub> see TR 054

<sup>2)</sup> For V<sub>Rk,s</sub> see Annex C 2, Table C2; Calculation of V<sub>Rk,pb</sub> and V<sub>Rk,c</sub> see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC2**  
Characteristic values of resistance under tension and shear load

**Annex C 6**

**Brick type: Autoclaved Aerated Concrete AAC4**

**Table C7: Description**

Brick type	Autoclaved Aerated Concrete AAC4	
Bulk density [kg/dm <sup>3</sup> ]	0,50	
Compressive strength [N/mm <sup>2</sup> ]	4	
Code	EN 771-4	
Producer (country code)	e.g. Ytong (CZ)	
Brick dimensions [mm]	499 x 375 x 249	
Drilling method	Rotary drilling	

**Table C8: Installation parameter (Edge and spacing distances)**

Anchor size	Effective anchorage depth $h_{ef}$	Edge distance		Spacing $s_{cr} = s_{min\parallel} = s_{min\perp}$	Maximum installation torque $T_{inst,max}$ [Nm]
		$c_{min} = c_{cr}$	[mm]		
		240	270		
M8	80	120		300	
M10	90	135		300	
M12	100	150		300	2
M16	100	150		300	

**Table C9: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
		[mm]	[mm]		[mm]	[mm]
80	$N_{Rk}$	0,23	0,47	$V_{Rk}$	1,23	1,84
90		0,58	1,17		0,87	1,31
100	$1,4 \cdot \gamma_M$	0,10	0,21	$1,4 \cdot \gamma_M$	1,29	1,94

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC4**

Brick description, drawing,  
Installation parameters, Displacement

**Annex C 7**

**Brick type: Autoclaved Aerated Concrete AAC4**

**Table C10: Characteristic values of resistance under tension and shear loads**

Anchor size	Effective anchorage depth  h <sub>ef</sub> [mm]	Characteristic resistance				
		Use conditions				
		d/d		w/d w/w		d/d w/d w/w
		40°C / 24°C		80°C / 50°C		For all temperature range
		N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	V <sub>Rk,b</sub> <sup>2)</sup>
<b>Compressive strength f<sub>b</sub> ≥ 4 N/mm<sup>2</sup></b>		[kN]				
<b>M8</b>	80	0,9	0,9	0,9	0,9	1,5
<b>M10</b>	90	2,5	2,0	1,5	1,5	2,0
<b>M12</b>	100	2,5	2,0	2,0	1,5	2,5
<b>M16</b>	100	3,5	3,0	2,0	2,0	3,5

<sup>1)</sup> For design according TR 054: N<sub>Rk</sub> = N<sub>Rk,p</sub> = N<sub>Rk,b</sub>; N<sub>Rk,s</sub> according to Table C2 Annex C2; Calculation N<sub>Rk,pb</sub> see TR 054

<sup>2)</sup> For V<sub>Rk,s</sub> see Annex C 2, Table C2; Calculation of V<sub>Rk,pb</sub> and V<sub>Rk,c</sub> see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC4**  
Characteristic values of resistance under tension and shear load

**Annex C 8**

**Brick type: Autoclaved Aerated Concrete AAC6**

**Table C11: Description**

Brick type	Autoclaved Aerated Concrete AAC6	
Bulk density [kg/dm <sup>3</sup> ]	0,60	
Compressive strength [N/mm <sup>2</sup> ]	6	
Code	EN 771-4	
Producer (country code)	e.g. Porit (DE)	
Brick dimensions [mm]	499 x 240 x 249	
Drilling method	Rotary drilling	

**Table C12: Installation parameter (Edge and spacing distances)**

Anchor size	Effective anchorage depth	Edge distance	Spacing	Maximum installation torque
				$T_{inst,max}$
	$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min\parallel} = S_{min\perp}$	[Nm]
<b>M8</b>	80	120	240	2
	<b>M10</b>	90	270	
	<b>M12</b>	100	300	
	<b>M16</b>	100	300	

**Table C13: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,54	1,09	$V_{Rk}$	0,32	0,48
90	$1,4 \cdot \gamma_M$	0,85	1,69	$1,4 \cdot \gamma_M$	1,49	2,23
100		0,10	0,19		1,67	2,50

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC6**  
Brick description, drawing,  
Installation parameters, Displacements

**Annex C 9**

**Brick type: Autoclaved Aerated Concrete AAC6**

**Table C14: Characteristic values of resistance under tension and shear loads**

Anchor size	Effective anchorage depth  h <sub>ef</sub> [mm]	Characteristic resistance							
		Use conditions							
		d/d		w/d w/w		d/d w/d w/w			
		40°C / 24°C		80°C / 50°C		40°C / 24°C			
		N <sub>Rk</sub> <sup>1)</sup>		N <sub>Rk</sub> <sup>1)</sup>		80°C / 50°C			
		For all temperature range							
		N <sub>Rk</sub> <sup>1)</sup>		N <sub>Rk</sub> <sup>1)</sup>		V <sub>Rk,b</sub> <sup>2)</sup>			
		[kN]							
<b>Compressive strength f<sub>b</sub> ≥ 6 N/mm<sup>2</sup></b>									
<b>M8</b>	80	2,0	2,0	2,0	2,0	5,5			
<b>M10</b>	90	3,0	2,5	2,5	2,0	9,0			
<b>M12</b>	100	4,5	3,5	3,0	2,5	9,0			
<b>M16</b>	100	5,5	4,5	3,5	3,0	11,0			

<sup>1)</sup> For design according TR 054: N<sub>Rk</sub> = N<sub>Rk,p</sub> = N<sub>Rk,b</sub>; N<sub>Rk,s</sub> according to Table C2 Annex C2; Calculation N<sub>Rk,pb</sub> see TR 054

<sup>2)</sup> For V<sub>Rk,s</sub> see Annex C 2, Table C2; Calculation of V<sub>Rk,pb</sub> and V<sub>Rk,c</sub> see TR 054


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Autoclaved Aerated Concrete – AAC6**  
Characteristic values of resistance under tension and shear load

**Annex C 10**

**Brick type: Calcium silicate solid brick KS-NF**

**Table C15: Description**

Brick type	Calcium silicate solid brick KS-NF	
Bulk density [kg/dm <sup>3</sup> ]	2,0	
Compressive strength [N/mm <sup>2</sup> ]	10, 20 or 27	
Code	EN 771-2	
Producer (country code)	e.g. Wemding (DE)	
Brick dimensions [mm]	240 x 115 x 71	
Drilling method	Hammer drilling	

**Table C16: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance		Spacing	Maximum installation torque
			$h_{ef}$	$C_{min} = C_{cr}$		
			[mm]			
M8	-	80	120	240	240	10
M10	-	90	135	270	270	20
M12 / M16	-	100	150	300	300	
M8	SH 12x80	80	120	240	240	10
	SH 16x85	85	127	255	255	
M10	SH 16x85	85	127	255	255	
M8 / M10	SH 16x130	130	195	390	390	20
	SH 16x130/330	130	195	390	390	
M12 / M16	SH 20x85	85	127	255	255	20
	SH 20x130	130	195	390	390	
	SH 20x200	200	300	600	600	

**Table C17: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$\frac{N_{Rk}}{1,4 \cdot \gamma_M}$	0,08	0,16	$\frac{V_{Rk}}{1,4 \cdot \gamma_M}$	3,07	4,61
85		0,26	0,52		1,46	2,19
90		0,09	0,18		1,50	2,25
100		0,10	0,20		1,03	1,53
130 ; 200		0,22	0,44		1,16	1,74

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Calcium solid brick KS-NF**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 11**

**Brick type: Calcium silicate solid brick KS-NF**

**Table C18: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth h <sub>ef</sub> [mm]	Characteristic resistance		
			Use conditions d/d; w/d; w/w		
			40°C / 24°C	80°C / 50°C	For all temperature range
			N <sub>Rk</sub> <sup>1)</sup>	N <sub>Rk</sub> <sup>1)</sup>	V <sub>Rk,b</sub> <sup>2)</sup>
<b>Compressive strength f<sub>b</sub> ≥ 10 N/mm<sup>2</sup></b>					
M8	-	80	3,0	2,0	3,0
M10	-	90	3,0	2,0	3,0
M12	-	100	4,0	2,5	3,5
M16	-	100	3,0	2,0	3,5
M8	SH 12x80	80	2,5	2,0	2,5
	SH 16x85	85	2,5	2,0	3,0
	SH16x130 / SH16x130/330	130	4,0	2,5	4,0
M10	SH 16x85	85	2,5	2,0	3,0
	SH16x130/330	130	4,5	3,0	4,0
M12 / M16	SH 20x85	85	2,5	2,0	3,0
	SH 20x130 / SH 20x200	130 / 200	4,5	2,5	4,0
<b>Compressive strength f<sub>b</sub> ≥ 20 N/mm<sup>2</sup></b>					
M8	-	80	4,5	3,0	4,5
M10	-	90	4,5	3,0	4,5
M12	-	100	5,5	3,5	5,0
M16	-	100	4,5	3,0	5,0
M8	SH 12x80	80	4,0	2,5	4,0
	SH 16x85	85	4,0	2,5	4,5
	SH16x130 / SH16x130/330	130	6,0	3,5	5,5
M10	SH 16x85	85	4,0	2,5	4,5
	SH 16x130/330	130	6,0	4,0	5,5
M12 / M16	SH 20x85	85	4,0	2,5	5,0
	SH 20x130 / SH 20x200	130 / 200	6,0	4,0	5,5
<b>Compressive strength f<sub>b</sub> ≥ 27 N/mm<sup>2</sup></b>					
M8	-	80	5,5	3,5	5,0
M10	-	90	5,5	3,5	5,5
M12	-	100	6,5	4,5	6,0
M16	-	100	5,5	3,5	6,0
M8	SH 12x80	80	4,5	3,0	4,5
	SH 16x85	85	4,5	3,0	5,5
	SH16x130 / SH16x130/330	130	6,5	4,5	6,5
M10	SH 16x85	85	4,5	3,0	5,5
	SH 16x130/330	130	6,5	4,5	6,5
M12 / M16	SH 20x85	85	4,5	3,0	5,5
	SH 20x130 / SH 20x200	130 / 200	6,5	4,5	6,5

<sup>1)</sup> For design according TR 054: N<sub>Rk</sub> = N<sub>Rk,p</sub> = N<sub>Rk,s</sub> according to Table C2 Annex C2; Calculation N<sub>Rk,pb</sub> see TR 054

<sup>2)</sup> For V<sub>Rk,s</sub> see Annex C 2, Table C2; Calculation of V<sub>Rk,pb</sub> and V<sub>Rk,c</sub> see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Calcium solid brick KS-NF**


Characteristic values of resistance under tension and shear load

**Annex C 12**

**Brick type: Calcium silicate hollow brick KS L-3DF**

**Table C19: Description**

Brick type	Calcium silicate hollow brick KS L-3DF	
Bulk density [kg/dm <sup>3</sup> ]	1,4	
Compressive strength [N/mm <sup>2</sup> ]	8, 12 or 14	
Code	EN 771-2	
Producer (country code)	e.g. Wemding (DE)	
Brick dimensions [mm]	240 x 175 x 113	
Drilling method	Rotary drilling	

**Table C20: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$c_{min} = c_{cr}$	$s_{cr} = s_{min \parallel}$	
				[mm]	[mm]	
M8	SH 12x80	80				
M8 / M10	SH 16x85	85	100	240	113	8
	SH 16x130	130				
	SH 16x130/330	130				
M12 / M16	SH 20x85	85	120			
	SH 20x130	130				
	SH 20x200	200				

**Table C21: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,36	0,73	$V_{Rk}$	0,82	1,23
85		1,62	3,24		1,83	2,75
130 ; 200	$1,4 \cdot \gamma_M$	1,70	3,40	$1,4 \cdot \gamma_M$	1,98	2,98

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Calcium hollow brick KS L-3DF**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 13**

**Brick type: Calcium silicate hollow brick KS L-3DF**

**Table C22: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d	w/d	w/w	
			40°C / 24°C	80°C / 50°C	For all temperature range	
		$h_{ef}$	$N_{Rk}^1)$	$N_{Rk}^1)$	$V_{Rk,b}^{2)}$	
		[mm]	[kN]			
<b>Compressive strength <math>f_b \geq 8 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	1,5	0,9	2,0	
	SH 16x85	85	1,5	0,9	2,5	
	SH 16x130	130	2,5	1,5	3,0	
	SH 16x130/330	130	2,5	1,5	3,0	
<b>M10</b>	SH 16x85	85	1,5	0,9	2,5	
	SH 16x130	130	2,5	1,5	3,0	
	SH 16x130/330	130	2,5	1,5	3,0	
<b>M12</b>	SH 20x85	85	1,5	0,9	3,0	
	SH 20x130 / SH 20x200	130 / 200	2,5	1,5	3,0	
<b>M16</b>	SH 20x85	85	1,5	0,9	3,0	
	SH 20x130 / SH 20x200	130 / 200	2,5	1,5	4,0	
<b>Compressive strength <math>f_b \geq 12 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	2,0	1,2	2,5	
	SH 16x85	85	2,0	1,2	3,5	
	SH 16x130	130	3,5	2,0	4,5	
	SH 16x130/330	130	3,5	2,0	4,5	
<b>M10</b>	SH 16x85	85	2,0	1,2	3,5	
	SH 16x130	130	3,5	2,0	4,5	
	SH 16x130/330	130	3,5	2,0	4,5	
<b>M12</b>	SH 20x85	85	2,0	1,2	3,5	
	SH 20x130 / SH 20x200	130 / 200	3,5	2,0	4,5	
<b>M16</b>	SH 20x85	85	2,0	1,2	3,5	
	SH 20x130 / SH 20x200	130 / 200	3,5	2,0	5,0	
<b>Compressive strength <math>f_b \geq 14 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	2,5	1,5	3,0	
	SH 16x85	85	2,5	1,5	4,0	
	SH 16x130	130	4,0	3,0	5,0	
	SH 16x130/330	130	4,0	3,0	5,0	
<b>M10</b>	SH 16x85	85	2,5	1,5	4,0	
	SH 16x130	130	4,0	3,0	5,0	
	SH 16x130/330	130	4,0	3,0	5,0	
<b>M12</b>	SH 20x85	85	2,5	1,5	4,5	
	SH 20x130 / SH 20x200	130 / 200	4,0	3,0	5,0	
<b>M16</b>	SH 20x85	85	2,5	1,5	4,5	
	SH 20x130 / SH 20x200	130 / 200	4,0	3,0	6,0	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Calcium hollow brick KS L-3DF**  
Characteristic values of resistance under tension and shear load

**Annex C 14**

## Brick type: Calcium silicate hollow brick KS L-12DF

**Table C23: Description**

Brick type	Calcium silicate hollow brick KS L-12DF	
Bulk density [kg/dm <sup>3</sup> ]	1,40	
Compressive strength [N/mm <sup>2</sup> ]	10, 12 or 16	
Code	EN 771-2	
Producer (country code)	e.g. Wemding (DE)	
Brick dimensions [mm]	498 x 175 x 238	
Drilling method	Rotary drilling	



**Table C24: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	
				[mm]	[mm]	[mm]
<b>M8</b>	SH 12x80	80				2
<b>M8 / M10</b>	SH 16x85	85	100	498	238	4
	SH 16x130	130				
	SH 16x130/330	130				
<b>M12 / M16</b>	SH 20x85	85	120			
	SH 20x130	130				

**Table C25: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
80						
	$N_{Rk}$	0,21	0,42			
85						
		0,13	0,26			
130						
	$1,4 \bullet \gamma_M$	0,22	0,44	$V_{Rk}$	1,77	2,66
					3,89	5,83
					4,35	6,52

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Calcium hollow brick KS L-12DF**

Brick description, drawing,  
Installation parameters, Displacement

**Annex C 15**

**Brick type: Calcium silicate hollow brick KS L-12DF**

**Table C26: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d	w/d	w/w	
			40°C / 24°C	80°C / 50°C	For all temperature range	
		$h_{ef}$	$N_{Rk}^{1)}$	$N_{Rk}^{1)}$	$V_{Rk,b}^{2)}$	
		[mm]		[kN]		
<b>Compressive strength <math>f_b \geq 10 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,4	0,3	3,0	
	SH 16x85	85	1,2	0,9	6,0	
	SH 16x130	130	3,5	2,5	7,0	
	SH 16x130/330	130	3,5	2,5	7,0	
<b>M10</b>	SH 16x85	85	1,2	0,9	6,0	
	SH 16x130	130	3,5	2,5	7,0	
	SH 16x130/330	130	3,5	2,5	7,0	
<b>M12 / M16</b>	SH 20x85	85	1,2	0,9	6,0	
	SH 20x130 / SH 20x200	130 / 200	3,5	2,5	7,0	
<b>Compressive strength <math>f_b \geq 12 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,4	0,3	3,5	
	SH 16x85	85	1,5	0,9	7,0	
	SH 16x130	130	4,5	3,0	8,0	
	SH 16x130/330	130	4,5	3,0	8,0	
<b>M10</b>	SH 16x85	85	1,5	0,9	7,0	
	SH 16x130	130	4,5	3,0	8,0	
	SH 16x130/330	130	4,5	3,0	8,0	
<b>M12 / M16</b>	SH 20x85	85	1,5	0,9	7,0	
	SH 20x130 / SH 20x200	130 / 200	4,5	3,0	8,0	
<b>Compressive strength <math>f_b \geq 16 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,5	0,4	4,0	
	SH 16x85	85	2,0	1,2	9,0	
	SH 16x130	130	5,5	3,5	10,0	
	SH 16x130/330	130	5,5	3,5	10,0	
<b>M10</b>	SH 16x85	85	2,0	1,2	9,0	
	SH 16x130	130	5,5	3,5	10,0	
	SH 16x130/330	130	5,5	3,5	10,0	
<b>M12 / M16</b>	SH 20x85	85	2,0	1,2	8,5	
	SH 20x130 / SH 20x200	130 / 200	5,5	3,5	10,0	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}; N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Calcium hollow brick KS L-12DF**

Characteristic values of resistance under tension and shear load

**Annex C 16**

**Brick type: Clay solid brick Mz-DF**

**Table C27: Description**

Brick type	Clay solid brick Mz-DF	
Bulk density [kg/dm <sup>3</sup> ]	1,64	
Compressive strength [N/mm <sup>2</sup> ]	10, 20 or 28	
Code	EN 771-1	
Producer (country code)	e.g. Unipor (DE)	
Brick dimensions [mm]	240 x 115 x 55	
Drilling method	Hammer drilling	

**Table C28: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing	Maximum installation torque
			$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min \parallel} = S_{min \perp}$
			[mm]		
<b>M8</b>	-	80	120	240	6
	SH 12x80	80	120	240	
	SH 16x85	85	127	255	
<b>M10</b>	-	90	135	270	10
<b>M12 / M16</b>	-	100	150	300	
<b>M10</b>	SH 16x85	85	127	255	
	SH 16x130	130	195	390	8
	SH 16x130/330	130	195	390	
<b>M12 / M16</b>	SH 20x85	85	127	255	8
	SH 20x130	130	195	390	
	SH 20x200	200	300	600	

**Table C29: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80		0,12	0,24		2,27	3,41
85		0,13	0,26		1,22	1,83
90		0,06	0,13		0,71	1,06
100		0,18	0,35		0,43	0,64
130 ; 200		0,42	0,85		1,22	1,83
	$N_{Rk}$			$V_{Rk}$		
	$1,4 \cdot \gamma_M$			$1,4 \cdot \gamma_M$		

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay solid brick Mz-DF**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 17**

**Brick type: Clay solid brick Mz-DF**

**Table C30: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions d/d; w/d; w/w		
			$h_{ef}$ [mm]	$N_{Rk}^{1)}$ [kN]	$N_{Rk}^{1)}$ [kN]
<b>Compressive strength <math>f_b \geq 10 \text{ N/mm}^2</math></b>					
M8	-	80	1,5	1,2	3,0
M10	-	90	1,5	1,2	3,5
M12	-	100	1,5	0,9	5,0
M16	-	100	2,5	1,5	5,0
M8	SH 12x80	80	2,0	1,5	3,0
	SH 16x85	85	2,0	1,5	3,0
	SH 16x130 / SH 16x130/330	130	3,0	2,0	3,0
M10	SH 16x85	85	2,0	1,5	3,5
	SH 16x130 / SH 16x130/330	130	3,0	2,0	3,5
M12 / M16	SH 20x85	85	2,0	1,5	3,5
	SH 20x130 / SH 20x200	130 / 200	3,0	2,0	3,5
<b>Compressive strength <math>f_b \geq 20 \text{ N/mm}^2</math></b>					
M8	-	80	2,5	1,5	4,5
M10	-	90	2,5	1,5	5,5
M12	-	100	2,0	1,5	7,5
M16	-	100	3,5	2,5	7,5
M8	SH 12x80	80	3,0	2,0	4,0
	SH 16x85	85	3,0	2,0	4,5
	SH 16x130 / SH 16x130/330	130	4,0	2,5	4,5
M10	SH 16x85	85	3,0	2,0	5,0
	SH 16x130 / SH 16x130/330	130	4,5	3,0	5,0
M12 / M16	SH 20x85	85	3,0	2,0	5,0
	SH 20x130 / SH 20x200	130 / 200	4,5	3,0	5,0
<b>Compressive strength <math>f_b \geq 28 \text{ N/mm}^2</math></b>					
M8	-	80	3,0	2,0	5,5
M10	-	90	3,0	2,0	6,5
M12	-	100	2,5	1,5	9,0
M16	-	100	4,5	3,0	9,0
M8	SH 12x80	80	3,5	2,5	5,0
	SH 16x85	85	3,5	2,5	5,0
	SH 16x130 / SH 16x130/330	130	5,0	3,5	5,0
M10	SH 16x85	85	3,5	2,5	6,0
	SH 16x130 / SH 16x130/330	130	5,0	3,5	6,0
M12 / M16	SH 20x85	85	3,5	2,5	6,0
	SH 20x130 / SH 20x200	130 / 200	5,0	3,5	6,0

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Clay solid brick Mz-DF**


Characteristic values of resistance under tension and shear load

**Annex C 18**

## Brick type: Clay hollow brick HLz-16DF

**Table C31: Description**

Brick type	Clay hollow brick HLz-16DF	
Bulk density [kg/dm <sup>3</sup> ]	0,83	
Compressive strength [N/mm <sup>2</sup> ]	6, 9, 12 or 14	
Code	EN 771-1	
Producer (country code)	e.g. Unipor (DE)	
Brick dimensions [mm]	497 x 238 x 240	
Drilling method	Rotary drilling	



**Table C32: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	
					$S_{cr} = S_{min \parallel}$	
				[mm]		[Nm]
M8	SH 12x80	80				
M8 / M10	SH 16x85	85	100	497	238	6
	SH 16x130	130				
	SH 16x130/330	130				
M12 / M16	SH 20x85	85	120			
	SH 20x130	130				
	SH 20x200	200				

**Table C33: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$		$\delta_{N\infty}$		$V$	$\delta_{v0}$	$\delta_{v\infty}$
		[mm]	[kN]	[mm]	[mm]			
80				0,27	0,55			
85				0,55	1,10			
130 ; 200				1,4 • $\gamma_M$	0,19	1,4 • $\gamma_M$	2,26	3,39

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick HLz-16DF**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 19**

**Brick type: Clay hollow brick HLz-16DF**

**Table C34: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions d/d; w/d; w/w		
			40°C / 24°C	80°C / 50°C	For all temperature range
			$h_{ef}$	$N_{Rk}^1)$	$N_{Rk}^1)$
		[mm]		[kN]	
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>					
<b>M8</b>	SH 12x80	80	1,2	0,75	2,5
	SH 16x85	85	1,5	1,2	4,0
	SH 16x130	130	2,5	1,5	4,0
	SH 16x130/330	130	2,5	1,5	4,0
<b>M10</b>	SH 16x85	85	1,5	1,2	4,0
	SH 16x130	130	2,5	1,5	6,0
	SH 16x130/330	130	2,5	1,5	6,0
<b>M12 / M16</b>	SH 20x85	85	2,0	1,5	4,0
	SH 20x130 / SH 20x200	130/ 200	2,5	1,5	6,0
<b>Compressive strength <math>f_b \geq 9 \text{ N/mm}^2</math></b>					
<b>M8</b>	SH 12x80	80	1,2	0,9	3,0
	SH 16x85	85	2,0	1,5	4,5
	SH 16x130	130	3,0	2,0	5,0
	SH 16x130/330	130	3,0	2,0	5,0
<b>M10</b>	SH 16x85	85	2,0	1,5	5,0
	SH 16x130	130	3,0	2,0	7,0
	SH 16x130/330	130	3,0	2,0	7,0
<b>M12 / M16</b>	SH 20x85	85	2,5	2,0	5,0
	SH 20x130 / SH 20x200	130/ 200	3,0	2,0	7,0
<b>Compressive strength <math>f_b \geq 12 \text{ N/mm}^2</math></b>					
<b>M8</b>	SH 12x80	80	1,5	1,2	3,5
	SH 16x85	85	2,5	1,5	5,5
	SH 16x130	130	3,5	2,5	6,0
	SH 16x130/330	130	3,5	2,5	6,0
<b>M10</b>	SH 16x85	85	2,5	1,5	6,0
	SH 16x130	130	3,5	2,5	8,0
	SH 16x130/330	130	3,5	2,5	8,0
<b>M12 / M16</b>	SH 20x85	85	3,5	2,0	6,0
	SH 20x130 / SH 20x200	130/ 200	3,5	2,5	8,0
<b>Compressive strength <math>f_b \geq 14 \text{ N/mm}^2</math></b>					
<b>M8</b>	SH 12x80	80	1,5	1,2	4,0
	SH 16x85	85	2,5	2,0	6,0
	SH 16x130	130	3,5	2,5	6,5
	SH 16x130/330	130	3,5	2,5	6,5
<b>M10</b>	SH 16x85	85	2,5	2,0	6,0
	SH 16x130	130	3,5	2,5	9,0
	SH 16x130/330	130	3,5	2,5	9,0
<b>M12 / M16</b>	SH 20x85	85	3,5	2,0	6,0
	SH 20x130 / SH 20x200	130/ 200	3,5	2,5	9,0

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}; N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick HLz-16DF**  
Characteristic values of resistance under tension and shear load

**Annex C 20**

## Brick type: Clay hollow brick Porotherm Homebric

**Table C35: Description**

Brick type	Clay hollow brick Porotherm Homebric	
Bulk density [kg/dm <sup>3</sup> ]	0,68	
Compressive strength [N/mm <sup>2</sup> ]	6, 8 or 10	
Code	EN 771-1	
Producer (country code)	e.g. Wienerberger (FR)	
Brick dimensions [mm]	500 x 200 x 299	
Drilling method	Rotary drilling	



**Table C36: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$c_{min} = c_{cr}$	
				[mm]	[mm]	
M8	SH 12x80	80				2
M8 / M10	SH 16x85	85	100	500	299	6
	SH 16x130	130				
	SH 16x130/330	130				
M12 / M16	SH 20x85	85	120			
	SH 20x130	130				

**Table C37: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,65	1,29	$V_{Rk}$	1,26	1,89
85		0,52	1,04		1,89	2,84
130	$1,4 \cdot \gamma_M$	0,45	0,90	$1,4 \cdot \gamma_M$	1,48	2,23

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Porotherm Homebric**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 21**

**Brick type: Clay hollow brick Porotherm Homebric**

**Table C38: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions d/d w/d w/w			
			40°C / 24°C	80°C / 50°C	For all temperature range	
		$h_{ef}$	$N_{Rk}^1)$	$N_{Rk}^1)$	$V_{Rk,b}^2)$	
		[mm]	[kN]			
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,9	0,75	2,0	
	SH 16x85	85	1,2	0,75	2,0	
	SH 16x130	130	1,5	0,9	2,5	
	SH 16x130/330	130	1,5	0,9	2,5	
<b>M10</b>	SH 16x85	85	1,2	0,75	2,0	
	SH 16x130	130	1,5	0,9	2,5	
	SH 16x130/330	130	1,5	0,9	2,5	
<b>M12</b>	SH 20x85	85	1,2	0,75	3,0	
	SH 20x130	130	1,5	0,9	3,0	
<b>M16</b>	SH 20x85	85	1,2	0,75	3,0	
	SH 20x130	130	1,5	0,9	3,0	
<b>Compressive strength <math>f_b \geq 8 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	1,2	0,9	2,5	
	SH 16x85	85	1,2	0,9	2,5	
	SH 16x130	130	1,5	1,2	3,0	
	SH 16x130/330	130	1,5	1,2	3,0	
<b>M10</b>	SH 16x85	85	1,2	0,9	2,5	
	SH 16x130	130	1,5	1,2	3,0	
	SH 16x130/330	130	1,5	1,2	3,0	
<b>M12</b>	SH 20x85	85	1,2	0,9	3,5	
	SH 20x130	130	1,5	1,2	3,5	
<b>M16</b>	SH 20x85	85	1,2	0,9	3,5	
	SH 20x130	130	1,5	1,2	3,5	
<b>Compressive strength <math>f_b \geq 10 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	1,2	0,9	3,0	
	SH 16x85	85	1,5	0,9	3,0	
	SH 16x130	130	2,0	1,2	3,5	
	SH 16x130/330	130	2,0	1,2	3,5	
<b>M10</b>	SH 16x85	85	1,5	0,9	3,0	
	SH 16x130	130	2,0	1,2	3,5	
	SH 16x130/330	130	2,0	1,2	3,5	
<b>M12</b>	SH 20x85	85	1,5	0,9	4,0	
	SH 20x130	130	2,0	1,2	4,0	
<b>M16</b>	SH 20x85	85	1,5	0,9	4,0	
	SH 20x130	130	2,0	1,2	4,0	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054



**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Porotherm Homebric**  
Characteristic values of resistance under tension and shear load

**Annex C 22**

**Brick type: Clay hollow brick BGV Thermo**

**Table C39: Description**

Brick type	Clay hollow brick BGV Thermo	
Bulk density [kg/dm <sup>3</sup> ]	0,62	
Compressive strength [N/mm <sup>2</sup> ]	4, 6 or 10	
Code	EN 771-1	
Producer (country code)	e.g. Leroux (FR)	
Brick dimensions [mm]	500 x 200 x 314	
Drilling method	Rotary drilling	
		

**Table C40: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing			Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min \parallel}$	
				[mm]	[mm]	[mm]	[mm]
M8	SH 12x80	80					2
M8 / M10	SH 16x85	85	100	500	314		4
	SH 16x130	130					
	SH 16x130/330	130					
	SH 20x85	85					
M12 / M16	SH 20x130	130	120				

**Table C41: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,27	0,54	$V_{Rk}$	1,21	1,81
85		0,39	0,77		2,00	3,01
130	$1,4 \cdot \gamma_M$	0,16	0,32	$1,4 \cdot \gamma_M$	1,60	2,39

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick BGV Thermo**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 23**

**Brick type: Clay hollow brick BGV Thermo**

**Table C42: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d	w/d	w/w	
			40°C / 24°C		80°C / 50°C	
		$h_{ef}$	$N_{Rk}^1)$		$V_{Rk,b}^2)$	
		[mm]	[kN]			
<b>Compressive strength <math>f_b \geq 4 \text{ N/mm}^2</math></b>						
M8	SH 12x80	80	0,5	0,4	2,0	
	SH 16x85	85	0,75	0,5	2,0	
	SH 16x130	130	0,9	0,75	2,5	
	SH 16x130/330	130	0,9	0,75	2,5	
M10	SH 16x85	85	0,75	0,5	2,0	
	SH 16x130	130	1,2	0,75	2,5	
	SH 16x130/330	130	1,2	0,75	2,5	
M12	SH 20x85	85	0,75	0,5	2,0	
	SH 20x130	130	1,2	0,75	2,5	
M16	SH 20x85	85	0,9	0,6	2,0	
	SH 20x130	130	1,2	0,75	2,5	
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>						
M8	SH 12x80	80	0,6	0,5	2,0	
	SH 16x85	85	0,9	0,6	2,5	
	SH 16x130	130	1,2	0,9	3,0	
	SH 16x130/330	130	1,2	0,9	3,0	
M10	SH 16x85	85	0,9	0,6	2,5	
	SH 16x130	130	1,5	0,9	3,0	
	SH 16x130/330	130	1,5	0,9	3,0	
M12	SH 20x85	85	0,9	0,6	3,0	
	SH 20x130	130	1,5	0,9	3,0	
M16	SH 20x85	85	1,2	0,75	3,0	
	SH 20x130	130	1,5	0,9	3,0	
<b>Compressive strength <math>f_b \geq 10 \text{ N/mm}^2</math></b>						
M8	SH 12x80	80	0,9	0,6	3,0	
	SH 16x85	85	1,2	0,9	3,5	
	SH 16x130	130	1,5	1,2	4,0	
	SH 16x130/330	130	1,5	1,2	4,0	
M10	SH 16x85	85	1,2	0,9	3,5	
	SH 16x130	130	1,5	1,2	4,0	
	SH 16x130/330	130	1,5	1,2	4,0	
M12	SH 20x85	85	1,2	0,75	3,5	
	SH 20x130	130	1,5	1,2	4,0	
M16	SH 20x85	85	1,5	0,9	3,5	
	SH 20x130	130	1,5	1,2	4,0	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}; N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick BGV Thermo**  
Characteristic values of resistance under tension and shear load

**Annex C 24**

## Brick type: Clay hollow brick Calibric Th

**Table C43: Description**

Brick type	Clay hollow brick Calibric Th	
Bulk density [kg/dm <sup>3</sup> ]	0,62	
Compressive strength [N/mm <sup>2</sup> ]	6, 9 or 12	
Code	EN 771-1	
Producer (country code)	e.g. Terreal (FR)	
Brick dimensions [mm]	500 x 200 x 314	
Drilling method	Rotary drilling	



500

200

14 40

86 20

6 5

**Table C44: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	
				[mm]	$S_{cr} = S_{min \parallel}$	
<b>M8</b>	SH 12x80	80				
<b>M8 / M10</b>	SH 16x85	85	100	500	314	2
	SH 16x130	130				
	SH 16x130/330	130				
	SH 20x85	85				
<b>M12 / M16</b>	SH 20x130	130	120			

**Table C45: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,48	0,96	$V_{Rk}$	1,18	1,78
85		0,49	0,98		2,20	3,30
130	$1,4 \cdot \gamma_M$	0,37	0,74	$1,4 \cdot \gamma_M$	2,31	3,46

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Calibric Th**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 25**

**Brick type: Clay hollow brick Calibric Th**

**Table C46: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d w/d w/w	40°C / 24°C	80°C / 50°C	
				For all temperature range		
		$h_{ef}$ [mm]	$N_{Rk}^1)$ [kN]	$N_{Rk}^1)$ [kN]	$V_{Rk,b}^2)$	
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,75	0,5	2,5	
	SH 16x85	85	0,75	0,5	3,5	
	SH 16x130	130	0,9	0,6	3,5	
	SH 16x130/330	130	0,9	0,6	3,5	
<b>M10</b>	SH 16x85	85	0,75	0,5	3,5	
	SH 16x130	130	0,9	0,6	3,5	
	SH 16x130/330	130	0,9	0,6	3,5	
<b>M12</b>	SH 20x85	85	0,75	0,5	6,0	
	SH 20x130	130	0,9	0,6	6,0	
<b>M16</b>	SH 20x85	85	1,2	0,75	6,0	
	SH 20x130	130	1,2	0,75	6,0	
<b>Compressive strength <math>f_b \geq 9 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,9	0,6	3,5	
	SH 16x85	85	0,9	0,6	4,5	
	SH 16x130	130	1,2	0,75	4,5	
	SH 16x130/330	130	1,2	0,75	4,5	
<b>M10</b>	SH 16x85	85	0,9	0,6	4,5	
	SH 16x130	130	1,2	0,9	4,5	
	SH 16x130/330	130	1,2	0,9	4,5	
<b>M12</b>	SH 20x85	85	0,9	0,6	7,5	
	SH 20x130	130	1,2	0,9	7,5	
<b>M16</b>	SH 20x85	85	1,5	0,9	7,5	
	SH 20x130	130	1,5	0,9	7,5	
<b>Compressive strength <math>f_b \geq 12 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	0,9	0,75	4,0	
	SH 16x85	85	0,9	0,75	5,5	
	SH 16x130	130	1,2	0,9	5,5	
	SH 16x130/330	130	1,2	0,9	5,5	
<b>M10</b>	SH 16x85	85	0,9	0,75	5,5	
	SH 16x130	130	1,5	0,9	5,5	
	SH 16x130/330	130	1,5	0,9	5,5	
<b>M12</b>	SH 20x85	85	0,9	0,75	8,5	
	SH 20x130	130	1,5	0,9	8,5	
<b>M16</b>	SH 20x85	85	1,5	1,2	8,5	
	SH 20x130	130	1,5	1,2	8,5	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick Calibric Th**  
Characteristic values of resistance under tension and shear load

**Annex C 26**

## Brick type: Clay hollow brick Urbanbrick

**Table C47: Description**

Brick type	Clay hollow brick Urbanbrick	
Bulk density [kg/dm <sup>3</sup> ]	0,74	
Compressive strength [N/mm <sup>2</sup> ]	6 or 9	
Code	EN 771-1	
Producer (country code)	e.g. Imerys (FR)	
Brick dimensions [mm]	560 x 200 x 274	
Drilling method	Rotary drilling	

**Table C48: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	
				$S_{cr} = S_{min\ II}$		
[mm]						
M8	SH 12x80	80				
M8 / M10	SH 16x85	85	100	560	274	2
	SH 16x130	130				
	SH 16x130/330	130				
M12 / M16	SH 20x85	85	120			
	SH 20x130	130				

**Table C49: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,34	0,67	$V_{Rk}$	0,71	1,06
85		0,52	1,04		1,37	2,06
130	$1,4 \cdot \gamma_M$	0,62	1,24	$1,4 \cdot \gamma_M$	1,62	2,44

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Urbanbrick**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 27**

**Brick type: Clay hollow brick Urbanbrick**

**Table C50: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d w/d w/w	40°C / 24°C	80°C / 50°C	
		$h_{ef}$	$N_{Rk}^1)$	$N_{Rk}^1)$	$V_{Rk,b}^2)$	
		[mm]	[kN]			
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>						
M8	SH 12x80	80	0,9	0,75	3,0	
M8 / M10	SH 16x85	85	1,2	0,75	3,5	
	SH 16x130	130	1,5	1,2	3,5	
M12 / M16	SH 16x130/330	130	1,5	1,2	3,5	
	SH 20x85	85	1,2	0,75	4,0	
	SH 20x130	130	1,5	1,2	4,0	
<b>Compressive strength <math>f_b \geq 9 \text{ N/mm}^2</math></b>						
M8	SH 12x80	80	1,2	0,9	3,5	
M8 / M10	SH 16x85	85	1,5	0,9	4,0	
	SH 16x130	130	2,0	1,5	4,5	
M12 / M16	SH 16x130/330	130	2,0	1,5	4,5	
	SH 20x85	85	1,5	0,9	5,0	
	SH 20x130	130	2,0	1,5	5,0	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}; N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick Urbanbrick**  
Characteristic values of resistance under tension and shear load

**Annex C 28**

## Brick type: Clay hollow brick Blocchi Leggeri

**Table C51: Description**

Brick type	Clay hollow brick Blocchi Leggeri	
Bulk density [kg/dm <sup>3</sup> ]	0,55	
Compressive strength [N/mm <sup>2</sup> ]	4, 6 or 8	
Code	EN 771-1	
Producer (country code)	e.g. Wienerberger (IT)	
Brick dimensions [mm]	250 x 120 x 250	
Drilling method	Rotary drilling	



**Table C52: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque	
				$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min \parallel}$	
				[mm]			
M8	SH 12x80	80					
M8 / M10	SH 16x85	85	100	250	250	4	
	SH 16x130	130					
	SH 16x130/330	130					
M12 / M16	SH 20x85	85	120				
	SH 20x130	130					
	SH 20x200	200					

**Table C53: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,32	0,64	$V_{Rk}$	1,16	1,74
85		0,26	0,53		2,52	3,78
130 ; 200	$1,4 \cdot \gamma_M$	0,32	0,64	$1,4 \cdot \gamma_M$	2,52	3,78

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Blocchi Leggeri**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 29**

**Brick type: Clay hollow brick Blocchi Leggeri**

**Table C54: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions		
			d/d w/d w/w	40°C / 24°C	80°C / 50°C
		$h_{ef}$	$N_{Rk}^{1)}$	$N_{Rk}^{1)}$	$V_{Rk,b}^{2)}$
		[mm]			[kN]
<b>Compressive strength <math>f_b \geq 4 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	0,4	0,3	2,0
M8 / M10	SH 16x85	85	0,4	0,3	2,0
	SH 16x130	130	0,5	0,3	2,0
M12 / M16	SH 16x130/330	130	0,5	0,3	2,0
	SH 20x85	85	0,4	0,3	2,0
	SH 20x130	130	0,5	0,3	2,0
M12 / M16	SH 20x200	200	0,5	0,3	2,0
<b>Compressive strength <math>f_b \geq 6 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	0,5	0,3	2,0
M8 / M10	SH 16x85	85	0,5	0,3	2,0
	SH 16x130	130	0,6	0,4	2,0
M12 / M16	SH 16x130/330	130	0,6	0,4	2,0
	SH 20x85	85	0,5	0,3	2,5
	SH 20x130	130	0,6	0,4	2,5
M12 / M16	SH 20x200	200	0,6	0,4	2,5
<b>Compressive strength <math>f_b \geq 8 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	0,6	0,4	2,5
M8 / M10	SH 16x85	85	0,6	0,4	2,5
	SH 16x130	130	0,6	0,5	2,5
M12 / M16	SH 16x130/330	130	0,6	0,5	2,5
	SH 20x85	85	0,6	0,4	3,0
	SH 20x130	130	0,6	0,5	3,0
M12 / M16	SH 20x200	200	0,6	0,5	3,0

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry**  
**POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick Blocchi Leggeri**  
Characteristic values of resistance under tension and shear load

**Annex C 30**

## Brick type: Clay hollow brick Doppio Uni

**Table C55: Description**

Brick type	Clay hollow brick Doppio Uni	
Bulk density [kg/dm <sup>3</sup> ]	0,92	
Compressive strength [N/mm <sup>2</sup> ]	10, 16, 20 or 28	
Code	EN 771-1	
Producer (country code)	e.g. Wienerberger (IT)	
Brick dimensions [mm]	250 x 120 x 120	
Drilling method	Rotary drilling	

**Table C56: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque	
				$h_{ef}$	$C_{min} = C_{cr}$	$S_{cr} = S_{min \parallel}$	
				[mm]			[Nm]
M8	SH 12x80	80					
M8 / M10	SH 16x85	85	100	250	120	4	
	SH 16x130	130					
	SH 16x130/330	130					
M12 / M16	SH 20x85	85	120				
	SH 20x130	130					
	SH 20x200	200					

**Table C57: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$		$\delta_{N\infty}$		$V$	$\delta_{V0}$		$\delta_{V\infty}$	
		[mm]	[kN]	[mm]	[mm]		[kN]	[mm]	[mm]	[mm]
80				0,54	1,08				1,63	2,45
85				0,17	0,34				1,75	2,63
130 ; 200			$1,4 \cdot \gamma_M$	0,54	1,08		$1,4 \cdot \gamma_M$		1,75	2,63

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Clay hollow brick Doppio Uni**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 31**

**Brick type: Clay hollow brick Doppio Uni**

**Table C58: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions d/d w/d w/w		
			40°C / 24°C	80°C / 50°C	For all temperature range
			$h_{ef}$ [mm]	$N_{Rk}^1)$ [kN]	$V_{Rk,b}^2)$
<b>Compressive strength <math>f_b \geq 10 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	0,9	0,6	2,0
M8 / M10	SH 16x85	85	0,9	0,6	2,0
	SH 16x130	130	0,9	0,6	2,0
M12 / M16	SH 16x130/330	130	0,9	0,6	2,0
	SH 20x85	85	1,2	0,75	2,0
	SH 20x130	130	1,2	0,75	2,0
M12 / M16	SH 20x200	200	1,2	0,75	2,0
	<b>Compressive strength <math>f_b \geq 16 \text{ N/mm}^2</math></b>				
M8	SH 12x80	80	0,9	0,75	2,5
M8 / M10	SH 16x85	85	1,2	0,9	2,5
	SH 16x130	130	1,2	0,9	2,5
M12 / M16	SH 16x130/330	130	1,2	0,9	2,5
	SH 20x85	85	1,5	0,9	2,5
	SH 20x130	130	1,5	0,9	2,5
M12 / M16	SH 20x200	200	1,5	0,9	2,5
<b>Compressive strength <math>f_b \geq 20 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	1,2	0,75	3,0
M8 / M10	SH 16x85	85	1,2	0,9	3,0
	SH 16x130	130	1,5	0,9	3,0
M12 / M16	SH 16x130/330	130	1,5	0,9	3,0
	SH 20x85	85	1,5	0,9	3,0
	SH 20x130	130	1,5	0,9	3,0
M12 / M16	SH 20x200	200	1,5	0,9	3,0
<b>Compressive strength <math>f_b \geq 28 \text{ N/mm}^2</math></b>					
M8	SH 12x80	80	1,5	0,9	3,5
M8 / M10	SH 16x85	85	1,5	1,2	3,5
	SH 16x130	130	1,5	1,2	3,5
M12 / M16	SH 16x130/330	130	1,5	1,2	3,5
	SH 20x85	85	2,0	1,2	3,5
	SH 20x130	130	2,0	1,2	3,5
M12 / M16	SH 20x200	200	2,0	1,2	3,5

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry**  
**POLIS, POLISB, POLIST, POLISE**


**Performance Clay hollow brick Doppio Uni**  
Characteristic values of resistance under tension and shear load

**Annex C 32**

**Brick type: Hollow Light weight concrete Bloc creux B40**

**Table C59: Description**

Brick type	Hollow light weight concrete Bloc creux B40	
Bulk density [kg/dm <sup>3</sup> ]	0,8	
Compressive strength [N/mm <sup>2</sup> ]	4	
Code	EN 771-3	
Producer (country code)	e.g. Sepa (FR)	
Brick dimensions [mm]	494 x 200 x 190	
Drilling method	Rotary drilling	

**Table C60: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance		Spacing		Maximum installation torque
			$h_{ef}$	$c_{min} = c_{cr}$	$s_{cr} = s_{min \parallel}$	$s_{min \perp}$	$T_{inst,max}$
			[mm]				
M8	SH 12x80	80					
M8 / M10	SH 16x85	85	100	494	190	2	
	SH 16x130	130					
	SH 16x130/330	130					
M12 / M16	SH 20x85	85	120				
	SH 20x130	130					

**Table C61: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,14	0,29	$V_{Rk}$	0,25	0,37
85		0,45	0,90		0,98	1,47
130	$1,4 \cdot \gamma_M$	0,61	1,22	$1,4 \cdot \gamma_M$	1,10	1,65

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance hollow light weight concrete Bloc creux B40**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 33**

**Brick type: Hollow Light weight concrete Bloc creux B40**

**Table C62: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions		
			d/d w/d w/w	40°C / 24°C	80°C / 50°C
		$h_{ef}$ [mm]	$N_{Rk}^1)$ [kN]	$N_{Rk}^1)$ [kN]	$V_{Rk,b}^2)$
<b>Compressive strength <math>f_b \geq 4 \text{ N/mm}^2</math></b>					
<b>M8</b>	SH 12x80	80	0,4	0,3	1,2
	SH 16x85	85	0,6	0,5	3,0
	SH 16x130	130	2,0	1,5	3,5
	SH 16x130/330	130	2,0	1,5	3,5
<b>M10</b>	SH 16x85	85	0,6	0,5	3,0
	SH 16x130	130	2,0	1,5	3,5
	SH 16x130/330	130	2,0	1,5	3,5
<b>M12</b>	SH 20x85	85	0,9	0,6	3,0
	SH 20x130	130	2,0	1,5	3,5
<b>M16</b>	SH 20x85	85	0,9	0,6	3,0
	SH 20x130	130	2,0	1,5	3,5

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054


**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance hollow light weight concrete Bloc creux B40**  
Characteristic values of resistance under tension and shear load

**Annex C 34**

**Brick type: Solid light weight concrete brick**

**Table C63: Description**

Brick type	Solid light weight concrete brick	
Bulk density [kg/dm <sup>3</sup> ]	0,63	
Compressive strength [N/mm <sup>2</sup> ]	2	
Code	EN 771-3	
Producer (country code)	e.g. Bisotherm (DE)	
Brick dimensions [mm]	300 x 123 x 248	
Drilling method	Rotary drilling	

**Table C64: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance		Spacing	Maximum installation torque
			$h_{ef}$	$C_{min} = C_{cr}$		
			[mm]			
M8	-	80	120	240		6
M10	-	90	135	270		
M12	-	100	150	300		
M16	-	100	150	300		14

**Table C65: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,64	1,28	$V_{Rk}$	0,50	0,75
90		0,70	1,41		0,68	1,03
100	$1,4 \cdot \gamma_M$	0,21	0,42	$1,4 \cdot \gamma_M$	0,54	0,81

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Solid light weight concrete LAC**

Brick description, drawing,  
Installation parameters, Displacements

**Annex C 35**

**Brick type: Solid light weight concrete brick**

**Table C66: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance		
			Use conditions d/d w/d w/w		
			40°C / 24°C	80°C / 50°C	For all temperature range
		$h_{ef}$ [mm]	$N_{Rk}^1)$	$N_{Rk}^1)$	$V_{Rk,b}^2)$ [kN]
<b>Compressive strength <math>f_b \geq 2 \text{ N/mm}^2</math></b>					
<b>M8</b>	-	80	2,0	1,5	3,0
<b>M10</b>	-	90	2,0	1,5	3,5
<b>M12</b>	-	100	2,0	1,5	4,0
<b>M16</b>	-	100	2,0	1,5	4,0

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}; N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance Solid light weight concrete LAC**  
Characteristic values of resistance under tension and shear load

**Annex C 36**

**Brick type: Hollow light weight concrete brick – Leca Lex harkko RUH-200**

**Table C67: Description**

Brick type	Hollow light weight concrete Leca Lex harkko RUH-200	
Bulk density [kg/dm <sup>3</sup> ]	0,7	
Compressive strength [N/mm <sup>2</sup> ]	2,7	
Code	EN 771-3	
Producer (country code)	e.g. Saint-Gobain Weber (Fin)	
Brick dimensions [mm]	498 x 200 x 195	
Drilling method	Rotary drilling	

**Table C68: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance	Spacing		Maximum installation torque
				$h_{ef}$	$C_{min} = C_{cr}$	
				$S_{cr} = S_{min \parallel}$		$T_{inst,max}$
[mm]				[mm]		
<b>M8</b>	SH 12x80	80	120	498	195	8
<b>M8 / M10</b>	SH 16x85	85	127			
	SH 16x130	130	195			
	SH 16x130/330	130	195			
<b>M12 / M16</b>	SH 20x85	85	127			
	SH 20x130	130	195			

**Table C69: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{V0}$	$\delta_{V\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$N_{Rk}$	0,11	0,22	$V_{Rk}$	0,47	0,70
85		0,11	0,23		0,38	0,57
130	$1,4 \cdot \gamma_M$	0,10	0,20	$1,4 \cdot \gamma_M$	0,56	0,85

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance LECA LEX harkko RUH-200 Hollow  
Brick description, drawing,  
Installation parameters, Displacements**

**Annex C 37**

**Brick type: Hollow light weight concrete brick – Leca Lex harkko RUH-200**

**Table C70: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth	Characteristic resistance			
			Use conditions			
			d/d w/d w/w	40°C / 24°C	80°C / 50°C	
		$h_{ef}$	$N_{Rk}^1)$	$N_{Rk}^1)$	$V_{Rk,b}^2)$	
		[mm]	[kN]			
<b>Compressive strength <math>f_b \geq 2,7 \text{ N/mm}^2</math></b>						
<b>M8</b>	SH 12x80	80	2,0	1,2	2,5	
	SH 16x85	85	2,0	1,2	3,5	
	SH 16x130	130	2,5	1,5	3,5	
	SH 16x130/330	130	2,5	1,5	3,5	
<b>M10</b>	SH 16x85	85	2,0	1,5	3,5	
	SH 16x130	130	2,5	1,5	3,5	
	SH 16x130/330	130	2,5	1,5	3,5	
<b>M12</b>	SH 20x85	85	2,5	1,5	3,5	
	SH 20x130	130	2,5	1,5	3,5	
<b>M16</b>	SH 20x85	85	2,5	1,5	3,5	
	SH 20x130	130	2,5	1,5	3,5	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance LECA LEX harkko RUH-200 Hollow**  
Characteristic values of resistance under tension and shear load  
Displacement

**Annex C 38**

**Brick type: Solid light weight concrete brick – Leca Lex harkko RUH-200 kulma**

**Table C71: Description**

Brick type	Solid light weight concrete Leca Lex harkko RUH-200 kulma	
Bulk density [kg/dm <sup>3</sup> ]	0,78	
Compressive strength [N/mm <sup>2</sup> ]	3	
Code	EN 771-3	
Producer (country code)	e.g. Saint-Gobain Weber (Fin)	
Brick dimensions [mm]	498 x 200 x 195	
Drilling method	Rotary drilling	

**Table C72: Installation parameter (Edge and spacing distances)**

Anchor size	Sleeve	Embedment depth	Edge distance		Spacing	Maximum installation torque
			$h_{ef}$	$C_{min} = C_{cr}$		
			[mm]			
M8	-	80	120	240	240	6
M10	-	90	135	270	270	12
M12	-	100	150	300	300	14
M16	-	100	150	300	300	16
M8	SH 12x80	80	120	240	240	8
M8 / M10	SH 16x85	85	127	255	255	16
	SH 16x130	130	195	390	390	16
	SH 16x130/330	130	195	390	390	16
M12 / M16	SH 20x85	85	127	255	255	12
	SH 20x130	130	195	390	390	16

**Table C73: Displacement**

Effective anchorage depth $h_{ef}$	N	$\delta_{N0}$	$\delta_{N\infty}$	V	$\delta_{v0}$	$\delta_{v\infty}$
[mm]	[kN]	[mm]	[mm]	[kN]	[mm]	[mm]
80	$\frac{N_{Rk}}{1,4 \cdot \gamma_M}$	0,09	0,18	$\frac{V_{Rk}}{1,4 \cdot \gamma_M}$	0,48	0,72
85		0,07	0,15		0,77	1,15
90		0,13	0,26		0,26	0,39
100		0,13	0,23		0,36	0,54
130		0,10	0,21		0,68	1,01

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance LECA LEX harkko RUH-200 Kulma Solid**  
Brick description, drawing,  
Installation parameters, Displacements

**Annex C 39**

**Brick type: Solid light weight concrete brick – Leca Lex harkko RUH-200 kulma**

**Table C74: Characteristic values of resistance under tension and shear loads**

Anchor size	Sleeve	Effective anchorage depth $h_{ef}$ [mm]	Characteristic resistance			
			Use conditions d/d w/d w/w			
			40°C / 24°C	80°C / 50°C	For all temperature range	
		$N_{Rk}^1)$ [kN]	$N_{Rk}^1)$ [kN]	$V_{Rk,b}^2)$		
<b>Compressive strength <math>f_b \geq 3,0 \text{ N/mm}^2</math></b>						
M8	-	80	2,0	1,2	3,0	
M10	-	90	3,0	2,0	4,0	
M12	-	100	3,0	2,0	4,0	
M16	-	100	3,0	2,0	4,0	
M8	SH 12x80	80	2,0	1,2	3,0	
	SH 16x85	85	2,0	1,5	3,5	
	SH 16x130	130	3,0	2,0	4,0	
	SH 16x130/330	130	3,0	2,0	4,0	
M10	SH 16x85	85	2,0	1,5	3,5	
	SH 16x130	130	3,0	2,0	4,0	
	SH 16x130/330	130	3,0	2,0	4,0	
M12 / M16	SH 20x85	85	2,0	1,5	4,5	
	SH 20x130	130	3,0	2,0	4,5	

<sup>1)</sup> For design according TR 054:  $N_{Rk} = N_{Rk,p} = N_{Rk,b}$ ;  $N_{Rk,s}$  according to Table C2 Annex C2; Calculation  $N_{Rk,pb}$  see TR 054

<sup>2)</sup> For  $V_{Rk,s}$  see Annex C 2, Table C2; Calculation of  $V_{Rk,pb}$  and  $V_{Rk,c}$  see TR 054

**RESINA POLIESTER SIN ESTIRENO LUSAN for masonry  
POLIS, POLISB, POLIST, POLISE**

**Performance LECA LEX harkko RUH-200 Kulma Solid**  
Characteristic values of resistance under tension and shear load

**Annex C 40**